Damp sweeping equipment
Flexible mop preferably fitted with disposable, antistatic and/or pre-impregnated gauze strips

Mechanical cleaning equipment
Auto scrubber, rotocleaner or single-brush machine

Reconditioning varnish application equipment

Mechanical cleaning disk
3M (or equivalent) colour disks

**This reconditioning protocol can be applied to a defined area or to the entire room.
In any case, isolate the area for 48 hours (to allow the varnish to cross-link).**

		Equipment used	Cleaning products	Cleaning methods
Preparation of the floor	Mechanical cleaning		Alkaline detergent	• Damp sweeping • Mechanical washing with black disk at 300-450 rpm (with water recovery)
Reconditioning	Manual application		Reconditioning varnish	• Apply a first coat of varnish with a brush to the most damaged areas (scratches), followed by application with a medium-length roller (≈120g/m²) on the entire area to be reconditioned. • Leave to dry for 48 hours.
Daily cleaning		No change, follow the care protocol as recommended by Gerflor for each area		
Deep cleaning		No change, follow the care protocol as recommended by Gerflor for each area		

To offer you the best results in terms of hygiene and appearance, **Gerflor recommends that you use neutral and alkaline detergents with high wetting power** (complete spreading and cleaning of the entire floor surface).

Here is a non-exhaustive list of products recommended by the main manufacturers:

KIEHL : Profloor*, RS Nett**
TANA : Green care SR15*, Floor Cleaner S*, Clean Fresh*, Difotan*, Clean Extreme*, Innomat**

ECOLAB : Brial Clean S*
ROCHEX : Polystar*, Roctonic**
BUZIL : HC 43**
DrSCHUTZ : PU Reiniger**

DIVERSEY : Asset*
DREITURM : Multinetzer*, Goldreif (green)*, Goldreif (blue)*, Linorein**, D1 Neu**

*Neutral / **Alkaline

Reconditioning varnish:

BLANCHON : Intensiv Ultra mat

DrSCHUTZ : Super PU Siegel extra matt, Super PU Siegel Seidenmatt

RZ REINIGUNGS / PFLEGESYSTEME GmbH : Turbo Protect Zero extramatt