

## MIPOLAM ACCORD

**ASTM** F1913

ASTM F1913 Evercare<sup>™</sup> FloorScore<sup>®</sup>

core EPD


**MIPOLAM ACCORD** high performance homogeneous sheet flooring with a semi-directional, marbleized design offering the best performance in the industry with the revolutionary Evercare<sup>™</sup> surface treatment.

**Evercare** " introduced in 2011 as the latest improvement in polyurethane surface treatment obtained by UV laser cross-linking. The treatment shields floors from stains and chemical products used in the healthcare environments and increases the durability of the flooring.

## CONTRIBUTES TO A SUSTAINABLE ENVIRONMENT

- 100% REACH compliant
- Recycled Content 25%
- Extremely low VOC; 100 times better than idustry requirements
- ▶ FloorScore certified
- Third party certified product-specific Type III EPD available







## MIPOLAM ACCORD



<u>iiii</u> ASTM F1913 Evercare<sup>™</sup> FloorScore<sup>®</sup> EPD<sup>®</sup>

DESCRIPTION	STANDARDS	REQUIREMENTS	MIPOLAM ACCORD
PRODUCT DESCRIPTION			
Reference Specification	ASTM F1913	-	Meets Requirements
Construction			Homogeneous sheet vinyl flooring
Surface Treatment / Maintenance	-	-	Evercare ™/No wax for life
Gauge Total Thickness	ASTM F386	> 0.075"	0.08" (2.0 mm)
Wearlayer Thickness	ASTM F410		0.08" (2.0 mm)
Roll Width	-	-	6'6" (2 m)
Roll Length	-	-	66' (20 m)
Coverage / Roll	-	-	430.6 sqft (90 sqm)
Weight	-	-	0.58 lb/ft² (2850 g/m²)
PERFORMANCE		1	
Static Load (250 psi)	ASTM F970	≤ 0.005″	-0.002" (Meets Requirements)
Maximum Static Load Limit	ASTM F970	≤ 0.005″	Up to 2000lbs/sq inch
Abrasion	ASTM F510	-	≤ -0.05g
Indentation - Residual	ASTM 1914	≤ 0.007″	-0.005"
Flexibility	ASTM F137	> 1.5"	Meets Requirements
Chemical & Stain Resistance	ASTM F925	-	Excellent, Test results available upon request
Coefficient of Friction	ASTM D2047	-	0.56 (Meets Requirements)
Coefficient of Friction	ASTM C1028		0.83 (Meets Requirements)
Resistance to Heat	ASTM F1514	∆E≤ 8	Meets Requirements
Resistance to Light	ASTM F1515	∆E≤ 8	Meets Requirements
Fire Rating	ASTM E648	Class 1	Class 1
	CAN/ULC S102.2		Tested in accordance Meets Requirements
Dimensional Stability	-	-	
Impact Insulation Class (IIC)	ASTM E989		42
ENVIRONMENT HEALTH & SAFETY			
Naturally Bacteriostatic: Inhibits the spread MRSA, E. coli, S. aureus*	ISO 22196	-	Limits spread of infection at 99%
Allergen-Free	-	-	100% Allergen-Free
Plant Certifications	-	-	ISO 14001, ISO 9001 OHSAS 18001
Production Waste	MRc3 LEED v4	-	100% Manufacturing Waste Recycled
MATERIALS & RESOURCES, BUILDING PRODUCT DISCLOSU	RE & OPTIMIZATION (BI	POD)	
Sourcing of Raw Materials: Recycled Content	MRc3 LEED v4	-	25%
Restriction Use of Harmful Chemicals	MRc4 LEED v4	-	100% REACH Compliant
Environmental Product Declaration (EPD)	MRc2 LEED v4	-	Product-Specific Type III
Health Product Declaration (HPD)	Materials LEED v4	-	Self declared
MATERIALS & RESOURCES, INDOOR ENVIRONMENTAL QUA	LITY (IEQ)		
Indoor Air Quality / Low Emitting Materials	EQc2 LEED v4	-	FloorScore <sup>®</sup> Certified
TVOC after 28 Days	ISO 16000-6	-	< 10 µg/m³
WARRANTY	10-year limi	ted manufacturer warrar	ty when installed in accordance with Gerflor's installation instructions.

\*The implementation of an effective cleaning method is the best defense against the spread of infection.





**NO heavy metals,** CMR 1, or CMR 2







MIPOLAM 1937

samples@gerflorusa.com

877-437-3567

www.gerflorusa.com