

| DESCRIPTION | | | | |
|--|-----------------------------|--------------------|---|-------------------------|
| Total Thickness | EN ISO 24346 | mm | 2 | |
| Weight | EN ISO 23997 | g/m ² | 3480 | |
| Size | EN ISO 24342 | mm | 457x914 | 184x1219 |
| Number of planks /tiles and sqm per box | - | - | 9 / 3.76m ² | 15 / 3.36m ² |
| CLASSIFICATION | | | | |
| Norm/Product Specification | - | - | EN ISO 19322 | |
| European Classification | EN ISO 10874 | class | 34 – 43 | |
| Fire Rating | EN 13 501-1 | class | Bfl-s1 | |
| Static Electrical Propensity | EN 1815 | kV | < 2 | |
| Slip Resistance Wet | EN 16165 app. B (DIN 51130) | class | R10 | |
| PERFORMANCES | | | | |
| Wear Resistance | EN 660.2 | mm ³ | < 2.0 | |
| Room Impact | NF S 31074 | dB | 77 | |
| Impact sound insulation | EN ISO 717-2 | dB | 4 | |
| Dimensional stability (norm) | EN ISO 23999 | % | ≤ 0.25 | |
| Dimensional stability (average measured value) | - | % | ≤ 0.10 | |
| Residual Indentation | EN ISO 24343-1 | mm | ≤ 0.10 | |
| Castor chair test | ISO 4918 | - | OK | |
| Thermal Conductivity | EN ISO 10456 | W/(m.K) | 0.25 | |
| Colour Fastness | EN ISO 105-B02 | degree | ≥ 6 | |
| Surface Treatment | - | - | Protecshield™ | |
| Chemical Products Resistance | EN ISO 26987 | | OK | |
| ENVIRONMENT / INDOOR AIR QUALITY | | | | |
| TVOC after 28 days | ISO 16000-6 | µg/ m ³ | < 10 | |
| CE MARKING | | | | |
|  | EN 14041 | |    | |
| | | |  | |

