

DESCRIPTION

Total thickness	EN ISO 24346	mm	4.00		
Thickness of wear layer	EN ISO 24340	mm	0.55		
Weight	EN ISO 23997	g/m ²	7200		
Size	EN ISO 24342	mm	184 x 1219	305 x 610	610 x 610
Number of planks / tiles and sqm per box	-	-	8 / 1.79m ²	10 / 1.86 m ²	4 / 1.49 m ²

CLASSIFICATION

Norm/Product specification	-	-	EN ISO 10582		
European classification	EN ISO 10874	class	33 - 42		
Fire rating	EN 13 501-1	class	B _{fl} -s1		
Static electrical propensity	EN 1815	kV	< 2		
Slip resistance wet	DIN 51130	Class	R9		


PERFORMANCES

Wear Resistance	EN 660.2	mm ³	≤ 2.0		
Wear Group	-	group	T		
Type Binder content	EN ISO 10582	type	I		
Dimensional stability	EN ISO 23999	%	≤ 0.15		
Residual indentation	EN ISO 24343-1	mm	≤ 0.10		
Sound insulation	EN ISO 717-2	dB	4		
Room impact noise	NFS 31074	dB	75		
Castor chair test (Type W)	ISO 4918	-	OK		
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25		
Colour fastness	EN 20 105 - B02	degree	≥ 6		
Surface treatment	-	-	PUR+ MATT		
Chemical Products Resistance	EN ISO 26987	-	OK		

ENVIRONMENT – INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	<100		
--------------------	-------------	--------------------	------	--	--

CE MARKING

	EN 14041		