


DESCRIPTION			TREND	DESIGN
Total Thickness	EN ISO 24346	mm	2,50	
Thickness of the wearlayer	EN ISO 24340	mm	0,55	
Weight	EN ISO 23997	g/m ²	3'850	4'410
Size	EN ISO 24342	mm	457 mm x 914 mm – 9 tiles / 3,76m ² 610 mm x 610 mm – 9 tiles / 3,35m ² 184 mm x 1219 mm – 15 planks / 3,36m ² 152 mm x 762 mm – 33 planks / 3,82m ² 230 mm x 1500 mm – 9 planks / 3,11m ² 914 mm x 914 mm – 5 planks / 4,18 m ²	
Number of planks/tiles and sqm per box	-	-		
CLASSIFICATION				
Norm/Product Specification	-	-	EN ISO 10582	
European Classification	EN ISO 10874	class	33 - 42	
Fire Rating	EN 13 501-1	class	B _{fl} -s1	
Static Electrical Propensity	EN 1815	kV	< 2	
Slip Resistance Wet	EN 16165 app. B (DIN 51130)	class	R10	
PERFORMANCES				
Wear Resistance	EN 660.2	mm ³	< 2,0	
Wear Group	-	group	T	
Type Binder content	ISO 10582	group	I	
Room Impact	NF S 31074	dB	77	
Impact sound insulation	EN ISO 717-2	dB	4	
Dimensional stability (norm)	EN ISO 23999	%	≤ 0,25	
Dimensional stability (average measured value)	-	%	≤ 0,10	
Residual Indentation	EN ISO 24343-1	mm	≤ 0,10	
Castor chair test	ISO 4918	-	OK	
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25	
Thermal Resistance	EN ISO 10456	m ² .K/W	0,01	
Colour Fastness	EN ISO 105-B02	degree	≥ 6	
Surface Treatment	-	-	ProtecShield™	
Chemical Products Resistance	EN ISO 26987		OK	
ENVIRONMENT / INDOOR AIR QUALITY				
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10	
CE MARKING				
	EN 14041		