


DESCRIPTION			DESIGN				
Total Thickness	EN ISO 24346	mm	2				
Thickness of the wearlayer	EN ISO 24340	mm	0,30				
Weight	EN ISO 23997	g/m ²	3'460				
Size	EN ISO 24342	mm	457x914	610x610	184x1219	230x1500	Chevron 184x1219
Number of planks /tiles and sqm per box	-	-	9 / 3.76m ²	9 / 3.35m ²	15 / 3.36m ²	11 / 3.80m ²	Chevron 14 / 3.14m ²
CLASSIFICATION							
Norm/Product Specification	-	-	EN ISO 10582				
European Classification	EN ISO 10874	class	23 - 31				
Fire Rating	EN 13 501-1	class	Bfl-s1				
Static Electrical Propensity	EN 1815	kV	< 2				
Slip Resistance Wet	EN 16165 app. B (DIN 51130)	class	R10				
PERFORMANCES							
Wear Resistance	EN 660.2	mm ³	< 2.0				
Wear Group	-	group	T				
Type Binder content	ISO 10582	group	I				
Room Impact	NF S 31074	dB	77				
Impact sound insulation	EN ISO 717-2	dB	4				
Dimensional stability (norm)	EN ISO 23999	%	≤ 0,25				
Dimensional stability (average measured value)	-	%	≤ 0,10				
Residual Indentation	EN ISO 24343-1	mm	≤ 0,10				
Castor chair test	ISO 4918	-	OK				
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25				
Thermal Resistance	EN ISO 10456	m ² .K/W	0,008				
Colour Fastness	EN ISO 105-B02	degree	≥ 6				
Surface Treatment	-	-	Protecshield™				
Chemical Products Resistance	EN ISO 26987		OK				
ENVIRONMENT / INDOOR AIR QUALITY							
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10				
CE MARKING							
	EN 14041		