


DESCRIPTION			
Total Thickness	EN ISO 24346	mm	2,50
Thickness of the wearlayer	EN ISO 24340	mm	0,55
Weight	EN ISO 23997	g/m ²	3'850 4'410
Size	EN ISO 24342	mm	152 x 762 mm / 33 / 3,82m ² 496 x 996 mm / 8 / 3,96m ² 184 x 1219 mm / 15 / 3,36m ²
Number of planks/tiles and sqm per box	-	pcs / m ²	230 x 1500 mm / 9 / 3,11m ² 610 x 610 mm / 9 / 3,35m ² 184 x 1219 mm (EIR) / 15 / 3,36m ² 230 x 1500 mm (EIR) / 9 / 3,11m ²
CLASSIFICATION			
Norm/Product Specification	-	-	EN ISO 10582
European Classification	EN ISO 10874	class	33 - 42
Fire Rating	EN 13 501-1	class	B _{fl} -s1
Static Electrical Propensity	EN 1815	kV	< 2
Slip Resistance Wet	EN 16165 app. B (DIN 51130)	class	R10
PERFORMANCES			
Wear Resistance	EN 660.2	mm ³	< 2,0
Wear Group	-	group	T
Type Binder content	ISO 10582	group	I
Room Impact	NF S 31074	dB	77
Impact sound insulation	EN ISO 717-2	dB	4
Dimensional stability (norm)	EN ISO 23999	%	≤ 0,25
Dimensional stability (average measured value)	-	%	≤ 0,10
Residual Indentation	EN ISO 24343-1	mm	≤ 0,10
Castor chair test	ISO 4918	-	OK
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25
Colour Fastness	EN ISO 105-B02	degree	≥ 6
Surface Treatment	-	-	PUR+ Matt
Chemical Products Resistance	EN ISO 26987		OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10
CE MARKING			
	EN 14041		