

DESCRIPTION

| | | | | | |
|--|--------------|------------------|--------------------------|--------------------------|--------------------------|
| Total Thickness | EN ISO24346 | mm | 4.35 | | |
| Thickness of the wearlayer | EN ISO24340 | mm | 0.70 | | |
| Weight | EN ISO 23997 | g/m ² | 3670 | | |
| Size | EN ISO 24342 | mm | 245 x 1250 | 150 x 750 | 500 x 500 |
| Number of planks / tiles and sqm per box | - | - | 11 / 3.37 m ² | 31 / 3.49 m ² | 15 / 3.75 m ² |

CLASSIFICATION

| | | | | | |
|--------------------------------|---------------------|---------------|--------------|--|--|
| Norm/Product Specification | - | - | EN ISO 11638 | | |
| European classification | EN ISO 10874 | classe | 34/42 | | |
| Fire rating | EN 13 501-1 | classe | Bfl-s1 | | |
| Static Electrical Propensity | EN 1815 | kV | < 2 | | |
| Slip Resistance Wet | DIN 51130 | classe | R10 | | |






PERFORMANCES

| | | | | | |
|---|---------------------|-----------------|----------------|--|--|
| Wear Resistance | EN 660.2 | mm ³ | ≤ 2.0 | | |
| Wear Group | QB 30 | groupe | T | | |
| Impact Sound Insulation | EN ISO 717-2 | dB | 20 | | |
| Room Impact | NFS 31 074 | dB | < 65 | | |
| Dimensional Stability (norm) | EN ISO 23999 | % | ≤ 0.25 | | |
| Dimensional Stability (average measure) | EN ISO 23999 | % | ≤ 0.03 | | |
| Residual Indentation (norm) | EN ISO 24343-1 | mm | ≤ 0.20 | | |
| Residual Indentation (average measure) | EN ISO 24343-1 | mm | 0.12 | | |
| Thermal Conductivity | EN ISO 10456 | W/(m.K) | 0.25 | | |
| Colour Fastness | EN 20 105 - B02 | degré | ≥ 6 | | |
| Chemical Products Resistance | EN ISO 26987 | classe | OK | | |
| Surface Treatment | - | - | ProtecShield™ | | |

ENVIRONMENT / INDOOR AIR QUALITY

| | | | | | |
|--------------------|-------------|--------------------|------|--|--|
| TVOC after 28 days | ISO 16000-6 | µg/ m ³ | < 10 | | |
|--------------------|-------------|--------------------|------|--|--|

MARQUAGE CE

| | | | |
|---|----------|---|---|
|  | EN 14041 | - |    |
| | | - |  |