


DESCRIPTION		DESIGN				
Total Thickness	EN ISO 24346	mm	2			
Thickness of the wearlayer	EN ISO 24340	mm	0,40			
Weight	EN ISO 23997	g/m <sup>2</sup>	3430			
Size	EN ISO 24342	mm	457,2 x 914,4	609,6 x 609,6	184,15 x 1219,2	230,0 x 1500,0
Number of planks /tiles and sqm per box	-	-	11 / 4,60 m <sup>2</sup>	13 / 4,83 m <sup>2</sup>	21 / 4,71 m <sup>2</sup>	13 / 4,49 m <sup>2</sup>
CLASSIFICATION						
Norm/Product Specification	-	-	EN ISO 10582			
European Classification	EN ISO 10874	class	23 - 32 - 41			
Fire Rating	EN 13 501-1	class	Bfl-s1			
Static Electrical Propensity	EN 1815	kV	< 2			
Slip Resistance Wet	EN 16165 app. B (DIN 51130)	class	R10			
PERFORMANCES						
Wear Resistance	EN 660.2	mm <sup>3</sup>	< 2,0			
Wear Group	-	group	T			
Type Binder content	ISO 10582	group	I			
Room Impact	NF S 31074	dB	77			
Impact sound insulation	EN ISO 717-2	dB	4			
Dimensional stability (norm)	EN ISO 23999	%	≤ 0,25			
Dimensional stability (average measured value)	-	%	≤ 0,10			
Residual Indentation	EN ISO 24343-1	mm	≤ 0,10			
Castor chair test	ISO 4918	-	OK			
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25			
Colour Fastness	EN ISO 105-B02	degree	≥ 6			
Surface Treatment	-	-	Protecshield™			
Chemical Products Resistance	EN ISO 26987		OK			
ENVIRONMENT / INDOOR AIR QUALITY						
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 10			
CE MARKING						
	EN 14041		