




DESCRIPTION			
Total thickness	EN ISO 24346	mm	2.00
Weight	EN ISO 23997	g/sq.m	2950
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	lm	20
	-	sq.m	40
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10581
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
	ASTM E648	class	Class I
Static electrical propensity	EN 1815	kV	≤ 2
PERFORMANCE			
Type Binder content	EN ISO 10581	type	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation	EN ISO 24343-1	mm	≤ 0.10
Castor chair test (type H)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105-B02	degree	≥ 6
Surface treatment	-	-	PUR+
Chemical products resistance	EN ISO 26987	class	OK
Anti-bacterial activity after 24h (E.coli – MRSA)*	ISO 22196	-	> 99 % inhibits growth
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 10
CE MARKING			
	EN 14041	-	
		-	

\*The implementation of an effective cleaning method is the best defense against infection