

DESCRIPTION

Total thickness	EN ISO24346	mm	2.00
Wearlayer thickness	EN ISO24340	mm	0.40
Weight	EN ISO 23997	g/m ²	2635
Width of sheet	EN ISO 24341	cm	300
Length of sheet	EN ISO 24341	m	20

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	32 - 41
Fire rating	EN 13 501-1	class	Cr-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet	EN 161652021 ppendi B (DIN 51 130)	class	R10





PERFORMANCE

Wear group	-	group	T
Type binder content	EN ISO 10582	group	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.10
Castor chair test (type W)	ISO 4918	-	OK
Conductivité thermique	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR +
Chemical product resistance	EN ISO 26987	class	OK

ENVIRONNEMENT / QUALITE DE L'AIR

TCOV after 28 days	ISO 16000-6	µg/ m ³	< 100
Certification	-	-	Floorscore® (in progress)

MARQUAGE CE

	EN 14041	-	  
---	----------	---	---