




DESCRIPTION			
Total thickness	EN ISO 24346	mm	2.30
	ASTM F386-02	inch	0.09
Wearlayer thickness	EN ISO 24340	mm	0.70
	ASTM F410-02	inch	0.028
Weight	EN ISO 23997	g/sq.m	3125
Width of sheet	EN ISO 24341	cm	200
	-	feet - inch	6'6"
Length of sheet	EN ISO 24341	lm	20
	-	feet - inch	65'7
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13 501-1	class	Br-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	EN 16165 app B	class	R10
PERFORMANCE			
Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	-	group	T
Type binder content	ISO 10582	Type	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Dimensional stability (average value measured)	-	%	0.03
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.10
Residual indentation (average value measured)	-	mm	≈ 0.03
Impact sound insulation	EN ISO 717-2	dB	8
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	Protecsol® 2
Chemical products resistance	EN ISO 26987	-	OK
Anti-bacterial activity (E. coli - S. aureus – MRSA) (1)	ISO 22196	-	> 99 % Inhibits growth
Antiviral activity (human coronavirus 229E) (1)	ISO 21702	-	99.7% after 2h
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10
Certification	-	-	Floorscore®
CE MARKING			
	EN 14041	-	
		-	

(1) The implementation of an effective cleaning regime is the best defence against infection