


DESCRIPTION						
Total Thickness	EN ISO 24346	mm	5.7			6
	ASTM F386	inch	0.22			0.24
Thickness of the wearlayer	EN ISO 24340	mm	0.55			0.55
	ASTM F410	inch	0.02			0.02
Weight	EN ISO 23997	g/m ²	7000			9480
Size	EN ISO 24342	mm	229 x 1492	229 x 1250	399 x 730	125 x 750
	ASTM F 536	inch	9.02 x 58.74	9.02 x 49.21	15.71 x 28.74	4.92 x 29.53
Number of planks /tiles and sqm per box	-	-	7 / 2.39 sqm	7 / 2 sqm	7 / 2.04 sqm	16 / 1.5 sqm
CLASSIFICATION						
Norm/Product Specification	-	-	EN ISO 10582			
	ASTM F 1700	-	Class III Type B			
European Classification	EN ISO 10874	class	23 – 33 – 42			
Fire Rating	EN 13 501-1	class	Bfl-s1			
Static Electrical Propensity	EN 1815	kV	< 2			
Slip Resistance Wet	EN 16165:2021 – Appendix B (DIN 51 130)	class	R10			
PERFORMANCES						
Wear Resistance	EN 660.2	mm ³	<2.0			
Wear Group	-	group	T			
Type Binder content	ISO 10582	group	I			
Room Impact	NF S 31074	dB	79			
Impact sound insulation	EN ISO 717-2	dB	21			
Dimensional stability (norm)	EN ISO 23999	%	≤ 0.15			
Dimensional stability (average measured value)	-	%	≤ 0.10			
Residual Indentation	EN ISO 24343-1	mm	≤ 0.10			
Castor chair test	ISO 4918	-	OK			
Thermal Conductivity	EN ISO 10456	W/(m.K)	0.25			
Colour Fastness	EN ISO 105 - B02	degree	≥ 6			
Surface Treatment	-	-	PUR+ MATT			
	EN ISO 26987		OK			
ENVIRONMENT / INDOOR AIR QUALITY						
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10			
CE MARKING						
	EN 14041		