


DESCRIPTION			
Total Thickness	EN ISO 24346	mm	5.7
Thickness of the wearlayer	EN ISO 24340	mm	0.55
Weight	EN ISO 23997	g/m <sup>2</sup>	7000
Size	EN ISO 24342	mm	229 x 1250
Number of planks and sqm per box/ Pallet	-	-	7 / 2.0 m <sup>2</sup> / 104 m <sup>2</sup>
CLASSIFICATION			
Norm/Product Specification	-	-	EN ISO 10582
	ASTM F 1700	-	Class III Type B
European Classification	EN ISO 10874	class	23 – 33 – 42
Fire Rating	EN 13 501-1	class	Bfl-s1
Static Electrical Propensity	EN 1815	kV	< 2
Slip Resistance Wet	EN 16165:2021 – Appendix B (DIN 51 130)	class	R10
PERFORMANCES			
Wear Resistance	EN 660.2	mm <sup>3</sup>	< 2.0
Wear Group	-	group	T
Type Binder content	ISO 10582	group	I
Room Impact	NF S 31074	dB	79
Impact sound insulation	EN ISO 717-2	dB	19
Dimensional stability (norm)	EN ISO 23999	%	≤ 0.15
Dimensional stability (average measured value)	-	%	≤ 0.15
Residual Indentation	EN ISO 24343-1	mm	≤ 0.10
Castor chair test	ISO 4918	-	OK
Thermal Conductivity	EN ISO 10456	W/(m.K)	0.25
Colour Fastness	EN ISO 105 - B02	degree	≥ 6
Surface Treatment	-	-	PUR+ Matt
Chemical Products Resistance	EN ISO 26987		OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 10
CE MARKING			
	EN 14041		