

DESCRIPTION

Total thickness	EN ISO24346	mm	3.10
Wearlayer thickness	EN ISO24340	mm	0.50
Poids	EN ISO 23997	g/m ²	2300
Weight	EN ISO 24341	cm	200 / 400
Width of sheet	EN ISO 24341	ml	≈ 25

CLASSIFICATION

Norm / Product specification	-	-	EN 651
European classification	EN ISO 10874	class	33 - 42
Impact sound insulation	EN ISO 717-2	dB	16
Walk noise	NFS 31 074	dB	< 65
Fire rating	EN 13 501-1	class	C _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	EN 16165:2021 – Appendix B (DIN 51 130)	class	R10





PERFORMANCE

Wear group	-	group	T
Dimensional stability (requirement)	EN ISO 23999	%	≤ 0.40
Dimensional stability (average measured value)	-	%	0.05
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.35
Residual indentation (average value measured)		mm	0.20
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Thermal resistance	EN 12664	m ² k/w	0.0124
Colour fastness	EN ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	Pureclean
Chemical products resistance	EN ISO 26987	class	OK

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100
Certification	-	-	Floorscore®

CE MARKING

	EN 14041	-	  
		-	