

DESCRIPTION

Total thickness	EN ISO24346	mm	2.00
Wearlayer thickness	EN ISO24340	mm	0.55
Weight	EN ISO 23997	g/m ²	2560
Width	EN ISO 24341	cm	200 / 400
Width of sheet	EN ISO 24341	ml	20

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	33-42
Impact sound insulation	EN ISO 717-2	dB	≈ 6
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	EN 16165:2021 – Appendix B (DIN 51 130)	class	R10





PERFORMANCE

Wear group	-	groupe	T
Dimensional stability (requirement)	EN ISO 10582	type	I
Dimensional stability (average measured value)	EN ISO 23999	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-2	mm	≤ 0.10
Residual indentation (average value measured)		mm	0.05
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degré	≥ 6
Surface treatment	-	-	PUR+
Chemical products resistance	EN ISO 26987	classe	OK

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100
Certification	-	-	Floorscore®

CE MARKING

	EN 14041	-	  
		-	