






DESCRIPTION			
Total thickness	EN ISO 24346	mm	2.00
Weight	EN ISO 23997	g/sqm	3100
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	lm	20
CLASSIFICATION			
Standard / Product specification		-	EN ISO 10581
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13501-1	class	Bfl-s1
Impact sound insulation	EN ISO 717-2	dB	5
Electrical resistance (1)	EN 1081	Ohm	$10^6 \leq R_t \leq 10^8$
Static electrical propensity	EN 1815	kV	< 2
Slip resistance	EN 16165:2021 – Appendix B (DIN 51 130)	Class	R9
PERFORMANCE			
Type Binder content	EN ISO 10581	type	II
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (norm)	EN ISO 24343-1	mm	≤ 0.10
Residual indentation (average measured value)	-	mm	~ 0.02
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105 - B02	degree	≥ 7
Surface treatment	-	-	Evercare™
Chemical products resistance	EN ISO 26987	-	OK
Anti viral activity (human coronavirus 229E)	ISO 21702		99.7% after 2h
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	$\mu\text{g}/\text{m}^3$	< 10
Certification	-	-	Floorscore®
MARQUAGE CE			
	EN 14041	-	  
		-	

(1) Measured before installation