

**DESCRIPTION**

|                     |              |                  |                 |
|---------------------|--------------|------------------|-----------------|
| Total thickness     | EN ISO24346  | mm               | 2.90            |
| Wearlayer thickness | EN ISO24340  | mm               | 0.35            |
| Weight              | EN ISO 23997 | g/m <sup>2</sup> | 2000            |
| Sheet width         | EN ISO 24341 | cm               | 200 / 300 / 400 |
| Sheet length        | EN ISO 24341 | ml               | ≈ 25            |

**CLASSIFICATION**

|  |   |       |                     |
|--|---|-------|---------------------|
| Norm / Product specification             | -                                       | -     | EN ISO 26986        |
| European classification                  | EN ISO 10874                            | class | 23 - 31             |
| Impact sound insulation                  | EN ISO 717-2                            | dB    | 16                  |
| Walk noise                               | NFS 31 074                              | dB    | < 65                |
| Fire rating                              | EN 13 501-1                             | class | C <sub>fl</sub> -s1 |
| Static electrical propensity             | EN 1815                                 | kV    | < 2                 |
| Slip resistance wet : ramp test with oil | EN 16165:2021 – Appendix B (DIN 51 130) | class | R10                 |




**PERFORMANCE**

|  |                  |         |        |
|--|------------------|---------|--------|
| Wear group                                     | -                | group   | T      |
| Dimensional stability (requirement)            | EN ISO 23999     | %       | ≤ 0.40 |
| Dimensional stability (average measured value) | -                | %       | 0.05   |
| Residual indentation (requirement)             | EN ISO 24343-2   | mm      | ≤ 0.35 |
| Residual indentation (average value measured)  |                  | mm      | 0.20   |
| Thermal conductivity                           | EN ISO 10456     | W/(m.K) | 0.25   |
| Colour fastness                                | EN ISO 105 - B02 | degree  | ≥ 6    |
| Surface treatment                              | -                | -       | GRIP'X |
| Chemical products resistance                   | EN ISO 26987     | class   | OK     |

**ENVIRONMENT / INDOOR AIR QUALITY**

|                    |             |                    |             |
|--------------------|-------------|--------------------|-------------|
| TVOC after 28 days | ISO 16000-6 | µg/ m <sup>3</sup> | < 100       |
| Certification      | -           | -                  | Floorscore® |

**CE MARKING**

|   |          |   |   |
|---|----------|---|---|
|  | EN 14041 | - |  |
|   |          | - |  |