

DESCRIPTION

Total thickness	EN ISO 24346	mm	2.00
	ASTM F386-02	inch	0.08
Weight	EN ISO 23997	g/sq.m	2630
Width of sheet	EN ISO 24341	cm	200
	-	feet - inch	6'6"
Length of sheet	EN ISO 24341 [EN 426]	lm	20
	-	feet - inch	66'
Coverage / roll	-	sq.ft	430.56
	-	sq.m	40

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 10581
	ASTM F 1913-04		compliant
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13 501-1	class	B _{fl} -s1
	ASTM E648-08	class	Class I
	CAN/ULC S102.2	-	tested in accordance
Static electrical propensity	EN 1815	kV	< 2






PERFORMANCE

Type Binder content	EN ISO 10581	type	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.10
Residual indentation (measure)	EN ISO 24343-1	mm	~ 0.02
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	Evercare™
Chemical products resistance (1)	EN ISO 26987	-	OK
Anti-bacterial activity (E.coli – S. aureus – MRSA) (2)	ISO 22196	-	> 99 % inhibits growth
Anti viral activity (human coronavirus 229E)	ISO 21702		99.7% after 2h 99.9% after 5h

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10
Certification	-	-	Floorscore®

CE MARKING

	EN 14041	-	  
		-	

(1) Regarding the resistance to chemicals, please download the corresponding leaflet from our web-site.

(2) The implementation of an effective cleaning method is the best defence against infection.