

DESCRIPTION

Total thickness	EN ISO 24346	mm	1.5
Weight	EN ISO 23997	g/sq.m	2520
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	lm	20

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 10581
European classification	EN ISO 10874	class	23-31
Fire rating	EN 13 501-1	class	Bi-s1
Static electrical propensity	EN 1815	kV	≤ 2





PERFORMANCE

Type Binder content	EN ISO 10581	type	II
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (norm)	EN ISO 24343-1	mm	≤ 0.10
Residual indentation (averagemeasured value)	-	mm	≈ 0.03
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR
Chemical products resistance	EN ISO 26987	class	OK

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10
--------------------	-------------	--------------------	------

CE MARKING

	EN 14041	-	  
		-	