




| DESCRIPTION  |                             |                    |   |
|--|-----------------------------|--------------------|---|
| Total Thickness  | EN ISO 24346                | mm                 | 7,8   |
| Thickness of the wearlayer   | EN ISO 24340                | mm                 | 0,70  |
| Weight   | EN ISO 23997                | g/m <sup>2</sup>   | 12 000  |
| Size   | EN ISO 24342                | mm                 | 457mm x 457mm   |
| Number of planks per box / sqm per box   | -                           | -                  | 5 / 1,04 sqm  |
| CLASSIFICATION   |                             |                    |   |
| Norm/Product Specification   | -                           | -                  | EN ISO 10582  |
| European Classification  | EN ISO 10874                | class              | 34 - 43   |
| Fire Rating  | EN 13 501-1                 | class              | B <sub>fl</sub> -s1   |
| Static Electrical Propensity   | EN 1815                     | kV                 | < 2   |
| Slip Resistance  | EN 16165 app. B (DIN 51130) | class              | R10   |
| PERFORMANCES   |                             |                    |   |
| Wear Resistance  | EN 660.2                    | mm <sup>3</sup>    | < 2,0   |
| Wear Group   | -                           | group              | T   |
| Type Binder content  | ISO 10582                   | group              | I   |
| Curling  | EN ISO 23999                | mm                 | ≤ 1   |
| Dimensional stability (norm)   | EN ISO 23999                | %                  | ≤ 0,15  |
| Residual Indentation   | EN ISO 24343-1              | mm                 | ≤ 0,05  |
| Castor chair test  | ISO 4918                    | -                  | OK  |
| Shore hardness   | EN ISO 868                  | H <sub>D</sub>     | > 60  |
| Thermal Conductivity   | EN ISO 10456                | W/(m.K)            | 0,25  |
| Colour Fastness  | EN ISO 105-B02              | degree             | ≥ 6   |
| Surface Treatment  | -                           | -                  | PUR+  |
| Chemical Products Resistance   | EN ISO 26987                |                    | OK  |
| ENVIRONMENT / INDOOR AIR QUALITY   |                             |                    |   |
| TVOC after 28 days   | ISO 16000-6                 | µg/ m <sup>3</sup> | < 100   |
| CE MARKING   |                             |                    |   |
|  | EN 14041                    |                    |   |
|  |                             |                    |  |