


DESCRIPTION					
Total Thickness	EN ISO 24346	mm	5	7	9
Thickness of the wearlayer	EN ISO 24340	mm	-		
Weight	EN ISO 23997	g/m ²	7000	9200	12800
Size	EN ISO 24342	mm	503 x 503		
Number of planks/tiles & sqm per box	-	-	10 / 2,53 sqm	8 / 2,02 sqm	6 / 1,52 sqm
CLASSIFICATION					
Norm/Product Specification	-	-	EN ISO 10581		
European Classification	EN ISO 10874	class	34 - 43		
Fire Rating	EN 13 501-1	class	B _{fl} -s1		
Static Electrical Propensity	EN 1815	kV	< 2		
Slip Resistance	EN 16165 app. B (DIN 51130)	class	R10		
PERFORMANCES					
Wear Resistance	EN 660.2	mm ³	< 2,0		
Type Binder content	ISO 10581	group	I		
Dimensional stability (norm)	EN ISO 23999	%	≤ 0,25		
Residual Indentation	EN ISO 24343-1	mm	≤ 0,10		
Castor chair test	ISO 4918	-	OK		
Flexibility	ISO 24344 method A		No cracking		
Shore hardness	EN ISO 868	H _b	≥ 40		
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25		
Colour Fastness	EN ISO 105-B02	degree	≥ 6		
Chemical Products Resistance	EN ISO 26987		OK		
ENVIRONMENT / INDOOR AIR QUALITY					
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100		
CE MARKING					
	EN 14041		