




| DESCRIPTION | | | |
|---|----------------------------------|-----------------|--|
| Total thickness | EN ISO 24346 | mm | 3.35 |
| Wearlayer thickness | EN ISO 24340 | mm | 0.65 |
| Weight | EN ISO 23997 | g/sq.m | 2825 |
| Width of sheet | EN ISO 24341 | cm | 200 |
| Length of sheet | EN ISO 24341 | lm | 25 |
| CLASSIFICATION | | | |
| Norm / Product specification | - | - | EN ISO 11638 |
| European classification | EN ISO 10874 | class | 34 - 42 |
| Fire rating | EN 13 501-1 | class | Bfl-s1 |
| Static electrical propensity | EN 1815 | kV | ≤2 |
| Slip resistance wet : ramp test with oil (1) | DIN EN 16165 annex B (DIN 51130) | class | R10 |
| PERFORMANCE | | | |
| Wear resistance | EN 660-2 | mm ³ | ≤ 2.0 |
| Wear group | EN 649 | group | T |
| Dimensional stability (requirement) | EN ISO 23999 | % | ≤ 0.40 |
| Residual indentation (requirement) | EN ISO 24343-1 | mm | ≤ 0.20 |
| Impact sound insulation | EN ISO 717-2 | dB | 19 dB |
| Castor chair test | ISO 4918 | - | OK |
| Thermal conductivity | EN ISO 10456 | W/(m.K) | 0.25 |
| Colour fastness | EN ISO 105-B02 | degree | ≥6 |
| Surface treatment | - | - | ProtecSol® |
| Chemical products resistance | EN ISO 26987 | - | OK |
| Anti-bacterial activity (E. coli - S. aureus) (2) | ISO 22196 | - | > 99 % Inhibits growth |
| ENVIRONMENT / INDOOR AIR QUALITY | | | |
| Certification | - | - | Floorscore® |
| CE MARKING | | | |
|  | EN 14041 | - |  |
| | | - |  |

(1) For lifetime sustainable wet resistance, please refer to Tarasafe ranges

(2) The implementation of an effective cleaning regime is the best defence against infection