

| DESCRIPTION 规格 | | | |
|---|----------------------------------|-----------------|---|
| Total thickness 总厚度 | EN ISO 24346 | mm | 3.35 |
| Thickness of the wearlayer 耐磨层厚度 | EN ISO 24340 | mm | 0.65 |
| Weight 重量 | EN ISO 23997 | g/sq.m | 2825 |
| Width of sheet 卷宽 | EN ISO 24341 | cm | 200 |
| Length of sheet 卷长 | EN ISO 24341 | lm | 25 |
| CLASSIFICATION 类别 | | | |
| Norm / Product specification 产品规范 | - | - | EN ISO 11638 |
| European classification 产品分级 | EN ISO 10874 | class | 34 - 42 |
| Fire rating 防火等级 | EN 13 501-1 | class | Bfl-s1 |
| | GB 8624-2012 | class | B ₁ |
| Static electrical propensity 抗静电性 | EN 1815 | kV | ≤2 |
| Slip resistance 防湿滑性 (1) | DIN EN 16165 annex B (DIN 51130) | class | R10 |
| PERFORMANCES 性能 | | | |
| Wear resistance 耐磨性 | EN 660-2 | mm ³ | ≤ 2.0 |
| Wear group 耐磨等级 | EN 649 | group | T |
| Dimensional stability 尺寸稳定性 | EN ISO 23999 | % | ≤ 0.40 |
| Residual indentation (requirement) 残余凹陷度 | EN ISO 24343-1 | mm | ≤ 0.20 |
| Impact sound insulation 隔音(隔声)性能 | EN ISO 717-2 | dB | 19 dB |
| Castor chair test 椅子脚轮测试 | ISO 4918 | - | OK |
| Thermal conductivity 热传导性 | EN ISO 10456 | W/(m.K) | 0.25 |
| Colour fastness 色牢度 | EN ISO 105-B02 | degree | ≥6 |
| Surface treatment 特殊维护处理 | - | - | ProtecSol® |
| Chemical products resistance 抗化学性 | EN ISO 26987 | - | OK |
| Anti-bacterial activity 抑菌性能 (E. coli - S. aureus 大肠杆菌和金黄色葡萄球菌) (2) | ISO 22196 | - | > 99 % 抑菌率 |
| ENVIRONMENT / INDOOR AIR QUALITY 环保/室内空气质量 | | | |
| Certification 证书 | - | - | Floorscore® |
| | GB 18586-2001 | - | OK |
| CE MARKING 标识 | | | |
|  | EN 14041 | - |  防滑  供地下暖气设备使用  抗静电  防火 |

(1) For lifetime sustainable wet resistance, please refer to Tarasafe ranges. 想获得终身持续的防湿滑性能·请参考Tarasafe系列。

(2) The implementation of an effective cleaning regime is the most important defence against infection. 实施有效的清洁方法是抗感染最重要的防御措施。