




| DESCRIPTION | | | |
|---|-------------------------------------|-----------------|---|
| Total thickness on grain side | EN ISO 24346 (EN 428) | mm | 2.00 |
| Wear layer thickness | EN ISO 24340 (EN 429) | mm | 1.00 |
| Weight | EN ISO 23997 (EN 430) | g/sq.m | 2400 |
| Width of sheet | EN ISO 24341 (EN 426) | cm | 200 |
| Length of sheet | EN ISO 24341 (EN 426) | lm | 20 |
| CLASSIFICATION | | | |
| Norm / Product specification | - | - | EN ISO 10582 (EN 649) |
| European classification | EN ISO 10874 (EN 685) | class | 34 - 43 |
| Fire rating | EN 13501-1 | class | Cfl-s1 |
| Static electrical propensity | EN 1815 | kV | ≤2 |
| Slip resistance wet: ramp test with oil | DIN EN 16165 annex B (DIN 51130) | class | R11 |
| PERFORMANCE | | | |
| Wear resistance | EN 660-2 | mm ³ | ≤ 4 |
| Wear group | EN 649 | group | P |
| Type Binder content | EN ISO 10582 | type | I |
| Dimensional stability | EN ISO 23999 (EN 434) | % | ≤ 0.40 |
| Residual indentation | EN ISO 24343-1 (EN 433) | mm | ≤ 0.10 |
| Castor chair test | ISO 4918 (EN 425) | - | OK |
| Thermal conductivity | EN ISO 10456 (EN 12524) | W/(m.K) | 0.25 |
| Colour fastness | EN ISO 105-B02 | degree | ≥6 |
| Chemical products resistance | EN ISO 26987 (EN 423) | - | OK |
| Anti-bacterial activity (MRSA) (1) | ISO 22196 | - | > 99 % inhibits growth |
| ENVIRONMENT / INDOOR AIR QUALITY | | | |
| Certification | - | - | Floorscore® |
| CE MARKING | | | |
|  | EN 14041 | - |  |
| | | - |  |

(1) The implementation of an effective cleaning method is the best defence against infection