


DESCRIPTION 规格			TREND	DESIGN
Total Thickness 总厚度	EN ISO 24346	mm	2,50	
Thickness of the wearlayer 耐磨层厚度	EN ISO 24340	mm	0,55	
Weight 重量	EN ISO 23997	g/m ²	3'850	4'410
Size 尺寸	EN ISO 24342	mm	457 mm x 914 mm – 9 tiles / 3,76m ² 610 mm x 610 mm – 9 tiles / 3,35m ² 184 mm x 1219 mm – 15 planks / 3,36m ² 152 mm x 762 mm – 33 planks / 3,82m ² 230 mm x 1500 mm – 9 planks / 3,11m ² 914 mm x 914 mm – 5 planks / 4,18 m ²	
Number of planks / tiles and sqm per box 片状数量及平米数/每箱				
CLASSIFICATION 类别				
Norm/Product Specification 产品规范	-	-	EN ISO 10582	
European Classification 产品分级	EN ISO 10874	class	33 - 42	
Fire Rating 防火等级	EN 13 501-1	class	B _{fl-s1}	
	GB 8624-2012	class	B ₁ (B-s ₁ ,t0)	
Toxic testing 有毒有害物质检测	GB 18586 - 2001	-	PASS	
Static Electrical Propensity 抗静电性	EN 1815	kV	≤2	
Slip Resistance Wet 防湿滑性	DIN EN 16165 annex B(DIN 51130)	class	R10	
PERFORMANCES 性能				
Wear Resistance 耐磨性	EN 660-2	mm ³	≤2.0	
Wear Group 耐磨等级	-	group	T	
Type Binder content 粘合物等级	ISO 10582	group	I	
Dimensional stability (norm) 尺寸稳定性	EN ISO 23999	%	≤ 0,25	
Residual Indentation 残余凹陷	EN ISO 24343-1	mm	≤ 0,10	
Castor chair test 椅子脚轮测试	ISO 4918	-	OK	
Thermal Conductivity 热传导性	EN ISO 10456	W/(m.K)	0,25	
Colour Fastness 颜色稳定性	EN ISO 105-B02	degree	≥ 6	
Surface Treatment 特殊维护处理	-	-	ProtecShield™	
Chemical Products Resistance 抗化学品性	EN ISO 26987		OK	
ENVIRONMENT / INDOOR AIR QUALITY 环保/室内空气质量				
TVOC after 28 days 28天后TVOC排放量	ISO 16000-6	µg/ m ³	< 10	
CE MARKING CE标志				
	EN 14041		