

DESCRIPTION			DESIGN				
Total Thickness	EN ISO 24346	mm	2				
Thickness of the wearlayer	EN ISO 24340	mm	0,30				
Weight	EN ISO 23997	g/m <sup>2</sup>	3'460				
Size	EN ISO 24342	mm	457x914	610x610	184x1219	230x1500	Chevron 184x1219
Number of planks /tiles and sqm per box	-	-	9 / 3.76m <sup>2</sup>	9 / 3.35m <sup>2</sup>	15 / 3.36m <sup>2</sup>	11 / 3.80m <sup>2</sup>	Chevron 14 / 3.14m <sup>2</sup>
CLASSIFICATION							
Norm/Product Specification	-	-	EN ISO 10582				
European Classification	EN ISO 10874	class	23 - 31				
Fire Rating	EN 13 501-1	class	Bfl-s1				
Static Electrical Propensity	EN 1815	kV	≤2				
Slip Resistance Wet	DIN EN 16165 annex B(DIN 51130)	class	R10				
PERFORMANCES							
Wear Resistance	EN 660-2	mm <sup>3</sup>	≤2.0				
Wear Group	-	group	T				
Type Binder content	ISO 10582	group	I				
Dimensional stability (norm)	EN ISO 23999	%	≤ 0,25				
Residual Indentation	EN ISO 24343-1	mm	≤ 0,10				
Castor chair test	ISO 4918	-	OK				
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25				
Colour Fastness	EN ISO 105-B02	degree	≥ 6				
Surface Treatment	-	-	Protecshield™				
Chemical Products Resistance	EN ISO 26987		OK				
ENVIRONMENT / INDOOR AIR QUALITY							
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 10				
CE MARKING							
<b>CE</b>	EN 14041						
							