


DESCRIPTION			
Total Thickness	EN ISO 24346	mm	5,00
Thickness of the wearlayer	EN ISO 24340	mm	0,70
Weight	EN ISO 23997	g/m <sup>2</sup>	8235
Size	EN ISO 24342	mm	701.3 x 701.3
Number of tiles and sqm per selling unit	-	-	20 / 9.83 sqm
CLASSIFICATION			
Norm/Product Specification	-	-	EN ISO 10582
European Classification	EN ISO 10874	class	34 - 43
Fire Rating	EN 13 501-1	class	Bfl-s1
Static Electrical Propensity	EN 1815	kV	≤2
Slip Resistance Wet	DIN EN 16165 annex B(DIN 51130)	class	R10
PERFORMANCES			
Wear Resistance	EN 660-2	mm <sup>3</sup>	≤2.0
Wear Group	-	group	T
Type Binder content	EN ISO 10582	group	I
Dimensional stability (norm)	EN ISO 23999	%	≤ 0.15
Residual Indentation	EN ISO 24343-1	mm	≤ 0.10
Castor chair test	ISO 4918	-	OK
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25
Colour Fastness	EN ISO 105-B02	degree	≥ 6
Surface Treatment	-	-	PUR+ Matt
Chemical Products Resistance	EN ISO 26987		OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 10
CE MARKING			
	EN 14041		