



## REACTION TO FIRE CLASSIFICATION REPORT N° 2021/209-2

According to EN 13501-1 (2018)

(English version of classification report N°2021/209-1)

Notification by the French Government to the European Commission  
under n° NB 2401  
Regulation (UE) n° 305/2011

Sponsor : GERFLOR  
50 Cours de la République  
69627 VILLEURBANNE CEDEX  
FRANCE

Product name : CREATION 40 TREND on SMART FIX 16 dB underlay

Description : Polyvinyl chloride floor coverings (EN ISO 10582 family)  
(see detailed description in paragraph 2)

Date of issue : 13/10/2021

*The indicated classification does not prejudice the conformity of marketed materials with the samples submitted to the tests and under no circumstances, this document should not be considered as type approval or certification of the product in the sense of the L 115-27 article of the consumption's code of the law dated June 3<sup>rd</sup> 1994.*

*The reproduction of this classification report is only authorised in its integral form.  
It comprises 4 pages*

## 1. Introduction

This classification report defines the classification assigned to the above-mentioned product in accordance with the procedures given in the NF EN 13501-1 standard (2018).

## 2. Details of classified product

### 2.1. Product standard

NF EN 14041 (2005):“Resilient, textile and laminate floor coverings - Essential characteristics”.

### 2.2. Product description

Heterogeneous polyvinyl chloride floor covering in size tiles and LVT of 457,2 mm x 914,4 mm – 609,6 mm x 609,6 mm – 184,15 mm x 1219,2 mm – 230 mm x 1500 mm (EN ISO 10582 family).

Use surface : PVC plastic.

Nominal mass per unit area : 3180 g/m<sup>2</sup>

Nominal total thickness : 2,0 mm

Nominal total wear layer : 0,40 mm

#### Underlay SMART FIX 16 dB

Nominal mass per unit area : 2000 g/m<sup>2</sup>

Nominal total thickness : 2,0 mm

Installation: Resilient floor covering CREATION 40 TREND tested loose laid on SMART FIX 16 dB underlay: together tested loose laid over a wood panel particle board without flame retarded classified C<sub>fl</sub>-s1 with a density (680 ± 50) kg/m<sup>3</sup> and thickness (20 ± 2) mm.

## 3. Test reports and tests results in support of this classification

### 3.1. Tests reports

Name of laboratory	Name of sponsor	Test report N°	Test method
C.R.E.T.	GERFLOR 50 Cours de la République 69627 VILLEURBANNE CEDEX	RL 2021/609-1	NF EN ISO 9239-1
		RL 2021/609-2	NF EN ISO 11925-2

### 3.2. Tests results

Test method	Product	Number of tests	Results	
			Parameters	Compliance parameters
NF EN ISO 11925-2	CREATION 40 TREND on SMART FIX 16 dB underlay	6	F <sub>s</sub> ≤ 150 mm	Compliant
Surface exposure-15 secondes			Ignition of the filter paper	Compliant

Test method	Product	Number of tests	Parameters	Results
				Continuous parameters : mean value
NF EN ISO 9239-1	CREATION 40 TREND on SMART FIX 16 dB underlay	3	Critical heat flux (kW/m <sup>2</sup> )	≥ 11
			Smoke (% X min)	152,7

#### 4. Classification and field of application

##### 4.1. Reference of classification

This classification has been carried out in accordance with EN 13501-1 (2018).

##### 4.2. Classification

Fire behaviour		Smoke production
B <sub>fl</sub>	-	s1

**Classification : B<sub>fl</sub> – s1**

##### 4.3. Field of application

This classification is valid for the following end use applications :

Loose laid and glued over a wood panel particle board without flame retarded classified C<sub>fl</sub>-s1, with a density ≥ 510 kg/m<sup>3</sup> and over a fibre-cement A2<sub>fl</sub>-s1 or A1<sub>fl</sub> class with a density ≥ 1350 kg/m<sup>3</sup>.

This classification is valid for the following product parameters :

##### **“CREATION 40 TREND”**

- A nominal mass per unit area of : 3180 g/m<sup>2</sup>
- A nominal thickness of : 2,0 mm
- A nominal thickness wear layer : 0,40 mm

##### **“SMART FIX 16 dB”underlay**

- A nominal mass per unit area of : 2000 g/m<sup>2</sup>
- A nominal thickness of : 2,0 mm

#### 5. Limitations


This classification document does not represent type approval or certification of the product.

“The classification assigned to the product in this report is appropriate to a declaration of conformity by the manufacturer within the context of system 3 of AVCP and CE marking under the Regulation 305/2011/EU of the European Parliament and of the Council of 9 March 2011 laying down harmonised conditions for the marketing of constructions products.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.”

Head of Tests  
David VANDIERDONCK



For the SARL C.R.E.T.  
The Technical Director  
Marc WELCOMME



*End of the classification report*