

TEST REPORT

TEST METHOD CONDUCTED	ASTM F410 Standard Test Method for Wear Layer Thickness of
	Resilient Floor Coverings by Optical Measurement

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Taraflex Sport M+

GENERAL PRINCIPLE

The thickness of the wear layer of resilient non-textile floor coverings is determined by microscopic optical measurement. The specimen is examined in five areas and measurements are made on the outer most layer of the composite material. The measurements are recorded to the .0001 inch and averaged.

TEST RESULTS

Specimen 1	0.0192 Inch	0.4877 mm
Specimen 2	0.0189 Inch	0.4801 mm
Specimen 3	0.0193 Inch	0.4902 mm
Specimen 4	0.0189 Inch	0.4801 mm
Specimen 5	0.0197 Inch	0.5004 mm
AVERAGE TOTAL THICKNESS	0.0192 Inch	0.4877 mm
	19.20 mil	

APPROVED BY: Jue Klullips

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us