

## TEST REPORT

DATE: 11-26-2024

Page 1 of 1

TEST NUMBER: 0312555

CLIENT	Gerflor The Flooring Group - France
--------	-------------------------------------

TEST METHOD CONDUCTED	ASTM F510 Standard Test Method for Resistance to Abrasion of Resilient Floor Coverings Using an Abrader with a Grit Feed Method
-----------------------	---

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Taraflex Sport M+

### GENERAL PRINCIPLE

A test specimen is subjected to the rubbing action of two abrading wheels under controlled conditions of pressure and abrasive action. The abrasion wheels rest on the surface of the specimen which is mounted on a rotating platform. Turning of the platform initiates the abrasive action on the test specimen.

### TEST RESULTS

WHEEL	S-39
LOAD APPLIED	1,000 Grams
NUMBER OF CYCLES	1,000
GRIT FEED SETTING	85

ORIGINAL WEIGHT	39.47 Grams
FINAL WEIGHT	39.41 Grams
WEIGHT LOSS	0.06 Grams (0.15%)

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.