

TEST REPORT

DATE: 11-26-2024

Page 1 of 1

TEST NUMBER: 0312555

CLIENT	Gerflor The Flooring Group - France
TEST METHOD CONDUCTED	ASTM F1914 Test Method for Short-Term Indentation and Residual Indentation of Resilient Floor Covering
DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Taraflex Sport M+

PROCEDURE

A test sample is loaded with 75 lbs. on a presser foot .250 inches in diameter for 15 minutes. After 60 minutes of recovery time the indentation is measured again and compared to the original thickness of the sample.

TEST RESULTS

RESIDUAL INDENTATION AT 75 Lbs.	0.015 Inch (5.17%)
---------------------------------	--------------------

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.