

DESCRIPTION

Total thickness	ISO 24346 (EN 428)	mm	2.0	2.1
Wearlayer thickness	ISO 24340 (EN 429)	mm	0.3	0.4
Weight	ISO 23997 (EN 430)	g/m ²	3150	3190
Width of sheet	ISO 24341 (EN 426)	cm	200	200
Length of sheet	ISO 24341 (EN 426)	lm	20	20

CLASSIFICATION

Norm / Product specification	-	-	ISO 10582 (EN 649)	ISO 10582 (EN 649)
European classification	ISO 10874 (EN 685)	class	23-31	23-31
Fire rating	EN 13 501-1	class	Bfl-s1	Bfl-s1
Static electrical propensity	EN 1815	KV	≤ 2	≤ 2
Slip resistance wet	DIN EN 16165	class	R9	R9

PERFORMANCES

Type binder content	ISO 10582	type	I	I
Dimensional stability	ISO 23999 (EN 434)	%	≤ 0.4	≤ 0.4
Residual indentation	ISO 24343-1 (EN 433)	mm	≤ 0.1	≤ 0.1
Castor chair test	ISO 4918 (EN 425)	-	OK	OK
Thermal conductivity	ISO 10456 (EN 12524)	W/(m.k)	0.25	0.25
Colour fastness	ISO 105 - B02	degree	≥ 6	≥ 6
Chemical product resistance	ISO 26987 (EN 423)	-	OK	OK
Surface treatment	-	-	PUR Protect	PUR Protect
Anti-bacterial activity (E.coli - S.aureus) ⁽¹⁾	ISO 22196	-	> 99% inhibits growth	> 99% inhibits growth

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000 - 6	µg/m ³	<100	<100
Certification	-	-	Floorscore®	Floorscore®

CE MARKING



EN 14041



(1) The implementation of an effective cleaning regime is the most important defence against infections.