

**DESCRIPTION**

Total thickness	EN ISO 24346	mm	4.00	
Wearlayer thickness	EN ISO 24340	mm	0.30	
Weight	EN ISO 23997	g/m <sup>2</sup>	7890	
Size	ISO 24342	mm	178x1219	457x914
Number of planks or tiles per box /sqm per box	-	-	8 / 1.73 m <sup>2</sup>	8 / 3.34 m <sup>2</sup>

**CLASSIFICATION**

Norm / Product specification	-	-	EN ISO 10582	
European classification	EN ISO 10874	class	23 - 31	
Fire rating	EN 13 501-1	class	Bfl-s1	
Static electrical propensity	EN 1815	kV	< 2	
Slip resistance wet (1)	DIN 51 130	class	R10	






**PERFORMANCES**

Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2.0	
Wear group	QB 30	group	T	
Type binder content	EN ISO 10582	Type	I	
Dimensional stability (norm)	EN ISO 23999	%	≤ 0.15	
Dimensional stability (average measured value)	-	%	≤ 0.08	
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.10	
Impact sound insulation	EN ISO 717-2	dB	4	
Room Impact	NF S 31074	dB	80	
Castor chair test (type W)	ISO 4918	-	OK	
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25	
Colour fastness	EN 20 105 - B02	degree	≥ 6	
Surface treatment	-	-	ProtecSheild™	
Chemical products resistance	EN ISO 26987	-	OK	

**ENVIRONMENT / INDOOR AIR QUALITY**

TVOC after 28 days	ISO 16000-6	µg/m <sup>3</sup>	< 100	
--------------------	-------------	-------------------	-------	--

**CE MARKING**

	<b>EN 14041</b>			
				

(1) Ramp test with oil

**IMPORTANT:** The information contained in this document is valid from 01/03/2023 and is subject to change at any time without notice. In the context of constantly changing technology, our customers are responsible prior to any use for checking with us that this document is the version in force.