

DESCRIPTION			
Total thickness	EN ISO 24346 [EN 428]	mm	2.00
Weight	EN ISO 23997 [EN 430]	g/sq.m	3300
Width of sheet	EN ISO 24341 [EN 426]	cm	200
Length of sheet	EN ISO 24341 [EN 426]	lm	20
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10581 (EN 649)
European classification	EN ISO 10874 (EN 685)	class	34 - 43
Fire rating	EN 13 501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance	DIN 51130 / BGR 181	Class	R9
PERFORMANCE			
Wear resistance	EN 660.2	mm ³	≤ 4.0
Wear Group	NF 189	group	P
Type Binder content	EN ISO 10581	type	II
Dimensional stability	EN ISO 23999 [EN 434]	%	≤ 0.40
Residual indentation	EN ISO 24343-1 [EN 433]	mm	≈ 0.03
Castor chair test (type W)	ISO 4918 (EN 425)	-	OK
Thermal conductivity	EN ISO 10456 (EN12524)	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR PROTECT
Chemical products resistance	EN ISO 26987 [EN 423]	class	OK
Anti-bacterial and fungicidal	-	-	OK
Color number	-	-	14
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10