

DESCRIPTION	TARASAFE		ULTRA	ULTRA H2O	STANDARD	H2O	SUPER
Total thickness	EN ISO 24346	mm	2.0	2.0	2.0	2.0	2.20
Thickness of wearlayer	EN ISO 24340	mm	1.16	1.0	0.85	0.85	1.12
Weight	EN ISO 23997	g/m ²	2460	2460	2460	2350	2880
Width/length of sheet	EN ISO 24341	cm/lm	200/20	200/20	200/20	200/20	200/20

CLASSIFICATION							
European classification	EN ISO 10874	class	34-43	34-43	34-43	34-43	34-43
Fire rating	AS ISO 9239-1	kW/m ² smoke %	8.3 134	8.5 112	8.4 199	8.9 132	8.7 167
Static Electrical Propensity	EN 1815	kV	<2	<2	<2	<2	<2
Slip Resistance wet pendulum	AS 4586 2013 (Appendix A)	class	P4	P3	P4	P5	P5
Slip resistance oil-wet ramp	AS 4586 2013 (Appendix D)	class	R10	R11	R10	R11	R12
Slip resistance wet/barefoot ramp	AS 4586 2013 (Appendix C)	class	-	C	-	B	-
Surface roughness	-	µm	Rz≥20	Rz≥20	Rz≥20	Rz≥20	Rz≥20

PERFORMANCE							
Abrasion resistance	EN 660.2	mm ³	≤2	≤4	≤2	≤2	≤2
Abrasion group	-	group	T	P	T	T	T
Dimensional stability	EN ISO 23999	%	≤0.40	≤0.40	≤0.40	≤0.40	≤0.40
Castor chair test (Type W)	ISO 4918	-	Good	Good	Good	Good	Good
Residual indentation	EN ISO	mm	≤0.03	≤0.10	≤0.05	≤0.10	≤0.10
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25	0.25	0.25	0.25	0.25
Colour fastness	EN 20	degree	≤6	≤6	≤6	≤6	≤6
Chemical products fastness	EN ISO 26987	-	Good	Good	Good	Good	Good
Surface treatment	-	-	SparClean ⁺	-	PUR	SparClean ⁺	-
Anti-bacterial activity MRSA(2)	ISO 22196	-	>99% inhibits bacteria growth	>99% inhibits bacteria growth	>99% inhibits bacteria	>99% inhibits bacteria	>99% inhibits bacteria growth

ENVIRONMENT							
TVOC	-	mg/m ³ /hr (24hr)	0.188	0.266	0.215	< 100	0.266
Global GreenTag			GreenRate	GreenRate	GreenRate	-	GreenRate

INSTALLATION should be carried out in accordance with local standards. The subfloor should be smooth, hard, clean, dry and free from contamination prior to laying. Where applicable the subfloor must incorporate an effective Damp Proof Membrane. The material must be allowed to acclimatise for 24 hours before installation, in a room temperature of between 18-24°C where the product will be installed.

MAINTENANCE should be carried out regularly to retain the appearance and durability of the floor. The floorcoverings should be maintained with regular sweeping and damp mopping. A more intense cleaning regime should be carried out periodically with a machine using a red pad and a neutral cleaner. No seals, polishes or waxes should be applied to the floorcovering, as this will impair the slip resistance of the floor.

ADHESIVES: Please refer to Gerflor installation guidelines on gerflor.com.au

IMPORTANT: Gerflor has a policy of continuous product and product data improvement. It reserves the right to change design and specifications without notice. The information contained in this document is valid from 01/01/2024 and is subject to change at any time without notice. In the context of constantly changing technology our customers are responsible, prior to any use, for checking with us that this document is the version in force.

To download the full Tarasafe range installation instructions, maintenance guides and certifications visit www.gerflor.com.au

Manufactured using recycled card.
A sampling service is available for your convenience - 1800 060 785
GERFLOR AUSTRALASIA PTY LTD
Tel +613 98321333
Email: custorders@gerflor.com.au



We care / we act Our commitments for a sustainable future




CARBON FOOTPRINT*
-20 % kg CO₂ equivalent/m² between 2020 and 2025


BIO-SOURCED CONTENT**
10 % by 2025


RECYCLED CONTENT
30 % by 2025


ADHESIVE FREE***
35 % by 2025


ANNUAL VOLUME RECYCLED
60 000 t by 2025

* Scopes 1 and 2 defined in the GHG protocol ** % of activity with biosourced materials *** % of activity - adhesive free solution