



## Gerflor CANADA Sport Products Adhesive Chart

GERFLOR SPORT PRODUCTS						ADHESIVE CHART - COVERAGE - MOISTURE LIMITS							
Adhesives	RH Limit (ASTM F2170)	CC Limit (ASTM F1869)	pH Limit	Size	Trowel notch	Coverage per pail or can of adhesive	Recreation Range	Taraflex Range	Sport M Comfort	Taraflex DTx	Isolsport	Vinyl Bleacher Blok	Surface to Bleacher Blok
Gerfix TPS+ (acrylic)	95%	10 lbs.	11	15.14 L.	1/32" x 1/16" x 1/32" 'U'	680 to 880 sq. ft./ pail	Green	Green	Red	Yellow	Yellow	Red	Red
Gerfix 196 (2 part Hybrid Acrylic)	98%	15 lbs.	12	9.46 L. (2.5 Gal)	1/32" x 1/16" x 1/32" 'U'	425 to 550 sq. ft./ pail	Green	Green	Green	Yellow	Green	Red	Red
Gerflor T-111 (polyurethane)	95%	8 lbs.	11	7.19 L.	1/32" x 1/16" x 1/32" 'U'	320 to 420 sq. ft./ pail	Red	Red	Red	Red	Yellow	Green	Green
Gerpur (urethane)	100%	25 lbs.	14	9.46 L.	1/16" x 1/16" x 1/16" Square	200 to 250 sq. ft./ pail	Red	Red	Red	Green	Red	Red	Red
Gerfix 100 (urethane)	100%	25 lbs.	14	7.57 L.	1/32" x 1/16" x 1/32" 'U'	340 to 440 sq. ft./ pail	Red	Red	Red	Red	Red	Green	Red

### Gerflor's Position on Moisture Testing

- Gerflor requires concrete slab moisture testing for any adhesive that is not rated for 100% RH
- Gerflor recognizes 2 methods to measure the moisture in a concrete slab: ASTM F2170 (RH) test and ASTM F1869 Calcium Chloride (CC) test
- It is always recommended to conduct both tests, and all tests need to meet the stated moisture limits
- If only one type of test is performed, Gerflor prefers the ASTM F2170 test method
- If Gerflor conducts an inspection on a moisture-related failure, we reserve the right to perform both tests

Colour Legend	
Green	= Approved
Yellow	= Needs Technical approval
Red	= NOT approved

Gerflor CANADA  
 214-1440 Hocquart  
 St-Bruno, QC H7T 0K5  
 844-437-3566  
 Email: gerflorcanada@gerflor.com  
 Website: gerflorcanada.com

Updated: January 2025