


DESCRIPTION			
Total Thickness	EN ISO 24346	mm	6
Thickness of the wearlayer	EN ISO 24340	mm	-
Weight	EN ISO 23997	g/m ²	8000
Size	EN ISO 24342	mm	456 x 456
Number of planks/tiles & sqm per box	-	-	6 / 1,25 m ²
CLASSIFICATION			
Norm/Product Specification	-	-	EN ISO 10581
European Classification	EN ISO 10874	class	34 / 43
Fire Rating	EN 13 501-1	class	B _{fl} -s1
Static Electrical Propensity	EN 1815	kV	< 2
Slip Resistance	EN 16165 app. B (DIN 51130)	class	R10
PERFORMANCES			
Wear Resistance	EN 660.2	mm ³	< 2,0
Type Binder content	ISO 10581	group	I
Dimensional stability (norm)	EN ISO 23999	%	≤ 0,25
Residual Indentation	EN ISO 24343-1	mm	≤ 0,10
Castor chair test	ISO 4918	-	OK
Flexibility	ISO 24344 method A		No cracking
Shore hardness	EN ISO 868	H _b	≥ 40
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25
Colour Fastness	EN ISO 105-B02	degree	≥ 6
Chemical Products Resistance	EN ISO 26987		OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100
CE MARKING			
	EN 14041		