

Gerflor® theflooringgroup		TARALAY EMOTION™ 添尉灵动™			
DESCRIPTION 规格					
Total thickness 总厚度	ISO 24346 (EN 428)	mm	2.0	2.6	2.0
Wearlayer thickness 耐磨层厚度	ISO 24340 (EN 429)	mm	0.7	0.7	0.55
Weight 重量	ISO 23997 (EN 430)	g/m²	2800	3800	2900
Width of sheet 卷宽	ISO 24341 (EN 426)	cm	200	200	200
Length of sheet 卷长	ISO 24341 (EN 426)	lm	20	15	20
CLASSIFICATION 类别					
Norm / Product specification 产品规范	-	-	ISO 10582 (EN 649)	ISO 10582 (EN 649)	ISO 10582 (EN 649)
European classification 产品分级	ISO 10874 (EN 685)	class	34-43	34-43	33-42
Fire rating 防火等级	EN 13501 - 1	class	Bfl-s1	Bfl-s1	Bfl-s1
	GB 8624 - 2012	class	B₁(B-s1, t0)	B₁(B-s1, t0)	B₁(B-s1, t0)
Toxic testing 有毒有害物质检测	GB 18586 - 2001	-	合格	合格	合格
Static electrical propensity 抗静电性	EN 1815	kV	≤ 2	≤ 2	≤ 2
Slip resistance wet 防湿滑性	DIN EN 16165	class	R9	R9	R9
PERFORMANCES 性能					
Type binder content 粘合物分级	ISO 10582	type	I	I	I
Dimensional stability 尺寸稳定性	ISO 23999 (EN 434)	%	≤ 0.4	≤ 0.4	≤ 0.4
Residual indentation 残余凹陷度	ISO 24343-1 (EN 433)	mm	≤ 0.1	≤ 0.1	≤ 0.1
Castor chair test 椅子脚轮测试	ISO 4918 (EN 425)	-	OK	OK	OK
Thermal conductivity 热传导性	ISO 10456 (EN 12524)	W/(m.k)	0.25	0.25	0.25
Colour fastness 颜色稳定性	ISO 105 - B02	degree	≥ 6	≥ 6	≥ 6
Chemical product resistance 抗化学性	ISO 26987 (EN 423)	-	OK	OK	OK
Special maintenance treatment 特殊维护处理	-	-	Protecsol®	Protecsol®	Protecsol®
Anti-bacterial activity 抑菌性能 (E.coli - S.aureus大肠杆菌和金黄色葡萄球菌) (1)	ISO 22196	-	> 99% inhibits growth 抑菌率	> 99% inhibits growth 抑菌率	> 99% inhibits growth 抑菌率
Antiviral activity (human coronavirus 229E) 抗病毒活性 (人类冠状病毒229E)	ISO 21702	-	99.7% (5小时)	99.7% (5小时)	99.7% (5小时)
ENVIRONMENT / INDOOR AIR QUALITY 环保 / 室内空气质量					
TVOC(2) after 28 days 28天后TVOC排放量	ISO 16000 - 6	µg/m³	< 100	< 100	< 100
Certification 证书	-	-	Floorscore®	Floorscore®	Floorscore®
CE MARKING 标识					
CE	EN 14041		DS   Bfl-s1		

Version No. CN2504

(1) The implementation of an effective cleaning regime is the most important defence against infections. 实施有效的清洁方法是抗感染最重要的防御措施。

(2) TVOC即挥发性有机化合物总排放量