




TARAFLEX® SPORT M PLUS

No. 1 SOLUTION FOR SPORT AND MULTIPURPOSE USE

Taraflex® Sport M Plus provides excellent levels of comfort and safety suited to all types of sports combined with some multipurpose activities.

- ASTM F2772 Class 3
- Superior Indentation Resistance: Improved shock absorption without sacrificing indentation resistance
- ▶ Absorption ball bounce: ≥ 96%
- ▶ Impact Protection Index (IPI): 76%
- Dual density foam
- No-wax for life—ease of maintenance
- Available with Gerflor Dry-Tex System
 - ▶ Highest moisture tolerance: 100% RH (25 lb)
 - ▶ Up to 70% cost savings compared to third party mitigation systems
 - Full-spread adhesive installation method: no risk of mold



6758	6873	6211	6570	4345
Silver Gray	Anthracite	Gold	Mint Green	Ecru
6038	6180	6557	2404	6445
Terracotta	Red	Forest	London Light Blue	Lagoon
6430	0012	6457	0003	6830
Blue	Navy Blue	Blueberry	Royal Blue	Black
5763	6375	6350	6391	7019
Maple Sun	Oak	Light Cherry	Wood Grey	Wood Crosscut
7020	4536	6390	4535	
Golden Herringbone	Wood Dark Blue	Wood Red	Wood Forest Green	

877.437.3567

TARAFLEX® SPORT M PLUS

DESCRIPTION	STANDARDS	REQUIREMENTS	WOOD DESIGNS	SOLID COLORS	MY TARAFLEX®			
PRODUCT DESCRIPTION								
Surface Treatment	-	-	₽rotëčšöl'					
Homogeneous Construction*	-	-	D-Mäx.					
Foam Backing	_	-	Double Density CXP ^{THD} +					
Total Thickness	-	-	0.30″ (7.5 mm)					
Total Top Layer	-	-	0.08" (2.1 mm)					
Weight	-	-	0.94 lb/ft² (4.6 kg/m²)					
Roll Width	-	-	4' 11" (1.5 m)					
Roll Length	-	-	86' 6" (26.4 m)	67' 3" (2	0.5 m)			
SPORT PROPERTIES								
Shock Absorption (Safety)	ASTM F2772	Class 1	Class 3					
Vertical Deformation	ASTM F2772	≤ 0.12″ (≤ 3 mm)	Pass					
Sliding Effect	ASTM F2772	80 - 110	Pass					
Ball Rebound	ASTM F2772	≥ 90%	≥ 96%					
Anti-Friction Burns	-	-	Protecsol.					
TECHNICAL CHARACTERISTICS								
Resistance to a Rolling Load	EN 1569	≥ 1500 N						
Chemical & Stain Resistance	ASTM F925	-	 Meets Requirements					
Fire Rating - Flame Spread	ASTM E648	Class 1						
Fire Rating - Flaming	ASTM E662	450 or less						
Fire Rating - Non-Flaming	ASTM E662	450 or less						
ENVIRONMENT HEALTH & SAFETY								
Bacterio-Static**	ISO 22196	-	Inhibits spread of infections at 99%					
Viro-Static**	ISO 21702	-	Inhibits growth of virus of 99.7% after 2 hours					
Manufacturing Plant Certifications	ISO 9001, 14001, 50001	-	Quality, Environment, Energy					
Environmental Product Declaration (EPD)	LEED v4 M+R	-	Product-Specific Type III					
Material Ingredients: Health Product Declaration (HPD)	LEED v4 M+R	-	Self-Declared					
No Harmful Chemicals	European Chemicals Agency (ECHA)	-	100% REACH Compliant					
Sourcing of Raw Material: Recycled Content	Average Pre-Consumer Content	-	34%					
Indoor Air Quality	California Standard 01350	-	FloorScore [®] Certified					
Production Waste	In-Plant Recycling	-	100% Manufacturing Waste Recycled					
TVOC after 28 days	ISO 16000-6	-	< 100µg/m²					
WARRANTY	15-year limited manufacturer warranty when installed in accordance with Gerflor's installation instructions							
Subbar leaves indelible stains on synthetic floorings. Do not use mats with rubbar backing and replace tubular furniture feat with these made of PVC or polyamide. Place mats of sufficient length of								

*Rubber leaves indelible stains on synthetic floorings. Do not use mats with rubber backing and replace tubular furniture feet with those made of PVC or polyamide. Place mats of sufficient length at entrances to reduce outside sources of dirt. **The best defense against the spread of infections is the implementation of an effective cleaning method.

877.437.3567