

**DESCRIPTION**

Total Thickness	EN ISO 24346	mm	3.4	
Thickness of the wearlayer	EN ISO 24340	mm	0.2	
Weight	EN ISO 23997	g/sqm	6750	
Size	EN ISO 24342	mm	177.8 x 1219.2	225 x 1524
Number of planks /tiles and sqm per box	-	-	9 planks / 1.95 sqm	6 planks / 2,06 sqm

**CLASSIFICATION**

Norm/Product Specification	-	-	EN ISO 10582	
European Classification	EN ISO 10874	class	22	
Fire Rating	EN 13 501-1	class	Bfl-s1	
Static Electrical Propensity	EN 1815	kV	< 2	
Slip Resistance Wet	DIN 51 130	class	R 9	


**PERFORMANCES**

Wear Resistance	EN 660.2	mm <sup>3</sup>	< 2.0	
Wear Group		group	T	
Type Binder content	ISO 10582	group	I	
Room Impact	NF S 31074	dB	4	
Impact sound insulation	EN ISO 717-2	dB	80	
Dimensional stability (norm)	EN ISO 23999	%	≤ 0.15	
Dimensional stability (average measured value)	-	%	≤ 0.10	
Residual Indentation	EN ISO 24343-1	mm	≤ 0.10	
Castor chair test	ISO 4918	-	OK	
Thermal Conductivity	EN ISO 10456	W/(m.K)	0.25	
Colour Fastness	EN 105 - B02	degree	≥ 6	
Surface Treatment	-	-	Pur+	
Chemical Products Resistance	EN ISO 26987		OK	

**ENVIRONMENT / INDOOR AIR QUALITY**

TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100	
--------------------	-------------	--------------------	-------	--

**CE MARKING**

	EN 14041		