

Gerflor®		DESIGN TILE		
DESCRIPTION				
Total Thickness	EN ISO 24346	mm	7,8	
Thickness of the wearlayer	EN ISO 24340	mm	0,70	
Weight	EN ISO 23997	g/m²	12 000	
Size	EN ISO 24342	mm	457mm x 457mm	614 mm x 614 mm
CLASSIFICATION				
Norm/Product Specification	-	-	EN ISO 10582	
European Classification	EN ISO 10874	class	34 - 43	
Fire Rating	EN 13 501-1	class	Bfl-s1	
Static Electrical Propensity	EN 1815	kV	< 2	
Slip Resistance	EN 16165 app. B (DIN 51130)	class	R10	
PERFORMANCES				
Wear Resistance	EN 660.2	mm³	< 2,0	
Wear Group	-	group	T	
Type Binder content	ISO 10582	group	I	
Curling	EN ISO 23999	mm	≤ 1	
Dimensional stability (norm)	EN ISO 23999	%	≤ 0,15	
Residual Indentation	EN ISO 24343-1	mm	≤ 0,05	
Castor chair test	ISO 4918	-	OK	
Shore hardness	EN ISO 868	H _D	> 60	
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25	
Colour Fastness	EN ISO 105-B02	degree	≥ 6	
Surface Treatment	-	-	PUR+	
Chemical Products Resistance	EN ISO 26987		OK	
ENVIRONMENT / INDOOR AIR QUALITY				
TVOC after 28 days	ISO 16000-6	µg/ m³	< 100	
CE MARKING				
CE	EN 14041		  	
				