

# TARASAFE

## STANDARD PUR - H<sub>2</sub>O - ULTRA - ULTRA H<sub>2</sub>O - SUPER

gerflor.au / follow us



DESCRIPTION			Tarasafe Ultra	Tarasafe Ultra H <sub>2</sub> O	Tarasafe Standard	Tarasafe H <sub>2</sub> O	Tarasafe Super
Total thickness	EN ISO 24346	mm	2.0	2.0	2.0	2.0	2.20
Thickness of wearlayer	EN ISO 24340	mm	0.85	1.0	0.85	0.85	1.12
Weight	EN ISO 23997	g/m <sup>2</sup>	2460	2460	2460	2350	2880
Width/length of sheet	EN ISO 24341	cm/lm	200/20	200/20	200/20	200/20	200/20

### CLASSIFICATION

European classification	EN ISO 10874	class	34-43	34-43	34-43	34-43	34-43
Fire rating	AS ISO 9239-1	kW/m <sup>2</sup>	9.2	8.5	10	8.9	8.7
		smoke%/min	140	112	119	132	167
Static electrical propensity	EN 1815	kV	≤ 2	< 2	< 2	< 2	< 2
Slip resistance wet pendulum	AS 4586 2013 (Appendix A)	class	P4	P3	P4	P5	P5
Slip resistance oil-wet ramp	AS 4586 2013 (Appendix D)	class	R10	R11	R10	R11	R12
Slip resistance wet/barefoot ramp	AS 4586 2013 (Appendix C)	class	-	C	-	B	-
Surface roughness	-	µm	Rz ≥ 20	Rz ≥ 20	Rz ≥ 20	Rz ≥ 20	Rz ≥ 20

### PERFORMANCE

Abrasion resistance	EN 660.2	mm <sup>3</sup>	≤ 2	≤ 4	≤ 2	≤ 2	≤ 2
Abrasion group	-	group	T	P	T	T	T
Dimensional stability	EN ISO 23999	%	≤ 0.40	≤ 0.40	≤ 0.40	≤ 0.40	≤ 0.40
Residual indentation	EN ISO 24343-1	mm	≤ 0.03	≤ 0.10	≈ 0.05	≤ 0.10	≤ 0.10
Castor chair test (type W)	ISO 4918	-	Good	Good	Good	Good	Good
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25	0.25	0.25	0.25	0.25
Colour fastness	EN ISO 105-B02	degree	≥ 6	≥ 6	≥ 6	≥ 6	≥ 6
Surface treatment	-	-	SparClean®	-	PUR	SparClean®	-
Chemical products fastness	EN ISO 26987	-	Good	Good	Good	Good	Good

### ENVIRONMENT / INDOOR AIR QUALITY

TVOC	-	mg/m <sup>2</sup> /hr (24 hours)	0.188	0.266	0.215	< 100	0.266
Certification	-	-	Floorscore®	Floorscore®	Floorscore®	Floorscore®	Floorscore®

(1) The implementation of an effective cleaning method is the best defence against infection.

**INSTALLATION** should be carried out in accordance with local standards. The subfloor should be smooth, hard, clean, dry and free from contamination prior to laying. Where applicable the subfloor must incorporate an effective Damp Proof Membrane. The material must be allowed to acclimatise for 24 hours before installation, in a room temperature of between 18-24°C where the product will be installed.

**MAINTENANCE** should be carried out regularly to retain the appearance and durability of the floor. The floorcoverings should be maintained with regular sweeping and damp mopping. A more intense cleaning regime should be carried out periodically with a machine using a red pad and a neutral cleaner. No seals, polishes or waxes should be applied to the floorcovering, as this will impair the slip resistance of the floor.

To download the full Tarasafe range installation instructions, maintenance guides and certifications visit [www.gerflor.com.au](http://www.gerflor.com.au)

**ADHESIVES:** Please refer to Gerflor Installation guidelines on [gerflor.com.au](http://gerflor.com.au)

**IMPORTANT** Gerflor has a policy of continuous product and product data improvement. It reserves the right to change design and specifications without notice. The information contained in this document is valid from 01/01/2024 and is subject to change at any time without notice. In the context of constantly changing technology our customers are responsible, prior to any use, for checking with us that this document is the version in force.

To download the full Tarasafe range installation instructions, maintenance guides and certifications visit [www.gerflor.com.au](http://www.gerflor.com.au)

Manufactured using recycled card.

A sampling service is available for your convenience -1800 060 785

GERFLOR AUSTRALASIA PTY LTD

Tel: +613 9832 1333

Email: [custorders@gerflor.com.au](mailto:custorders@gerflor.com.au)



### WE CARE | WE ACT our commitments for 2030



#### climate

-30% CO<sub>2</sub> scopes 1,2,3 in tons eq CO<sub>2</sub> vs 2019

Science Based Targets



#### resources

75% biobased, mineral, recycled content

30% recycled content



#### circularity

65,000 tons of waste recycled

45% loose lay



#### health & well-being

100% outperforming Indoor Air Quality standards

95% sales covered by EPDs



#### people

Towards 0 accidents

30% women

40% internal mobility

\*for further information please visit our website [www.gerflor.au](http://www.gerflor.au)