



REACTION TO FIRE CLASSIFICATION REPORT  
N°2025/217-2

According to EN 13501-1 (2018)

(English version of classification report N°2025/217-1)

Notification by the French Government to the European Commission  
under n° NB 2401  
Regulation (UE) n° 305/2011

Sponsor : GERFLOR  
1 Place Verrazzano  
69258 LYON Cedex 09  
FRANCE

Product name : CREATION 55 ARTE / TREND (site 004 and 008)

Description : Polyvinyl chloride floor coverings (EN ISO 10582 family)  
(see detailed description in paragraph 2)

Date of issue : 24/10/2025

*The indicated classification does not prejudice the conformity of marketed materials with the samples submitted to the tests and under no circumstances, this document should not be considered as type approval or certification of the product in the sense of the L 115-27 article of the consumption's code of the law.*

*The reproduction of this classification report is only authorised in its integral form.  
It comprises 4 pages*

## 1. Introduction

This classification report defines the classification assigned to the above-mentioned products in accordance with the procedures given in the NF EN 13501-1 standard (2018).

## 2. Details of classified product

### 2.1. Product standard

NF EN 14041 (2005):“ Resilient, textile and laminate floor coverings - Essential characteristics”.

### 2.2. Product description

Heterogeneous polyvinyl chloride floorcovering (EN ISO 10582 family) in size LVT and tile of 184,15 mm x 1219,2 mm – 208 mm x 1243 mm – 230 mm x 1500 mm – 152 mm x 762 mm – 457 mm x 914 mm – 496,5 mm x 496,5 mm – 496,5 mm x 996,5 mm – 610 mm x 610 mm.

Tested glued (acrylic glue with depositing 300 g/m<sup>2</sup>) over a wood panel particle board without flame retarded classified C<sub>n</sub>-s1 with a density (680 ± 50) kg/m<sup>3</sup> and thickness (20 ± 2) mm.

Use surface: Plasticized PVC

Nominal mass per unit area : 3850 g/m<sup>2</sup>

Nominal total thickness : 2,50 mm

Nominal total wear layer : 0,55 mm

## 3. Test reports and tests results in support of this classification

### 3.1. Tests reports

Name of laboratory	Name of sponsor	Test report N°	Test method
C.R.E.T.	GERFLOR 1 Place Verrazzano 69258 LYON Cedex 09 FRANCE	RL 2017/202	NF EN ISO 9239-1
		RL 2021/543-1	(EN ISO 9239-1 :2010)
		RL 2021/543-2	NF EN ISO 11925-2 (EN ISO 11925-2 :2020)

### 3.2. Tests results

Classes of reaction to fire for resilient floor coverings, classified without further testing.

Test method EN ISO 11925-2 (2010)	The flooring “ <b>CREATION 55 TREND (site 08)</b> ” meets the requirements of table 3 of the standard NF EN 14041 (2005) and is classified E <sub>n</sub> without further testing (CWFT)
--------------------------------------	--

Test method	Product	Number of tests	Results	
			Parameters	Compliance parameters
NF EN ISO 11925-2	CREATION 55 ARTE (site 004)	6	Fs ≤ 150 mm	Compliant
Surface exposure-15 secondes			Ignition of the filter paper	Compliant

Test method	Product	Number of tests	Parameters	Results
				Continuous parameters : mean value
NF EN ISO 9239-1	CREATION 55 TREND (site 008)	3	Critical heat flux (kW/m <sup>2</sup> )	8,6
			Smoke (% X min)	264,3

Test method	Product	Number of tests	Parameters	Results
				Continuous parameters : mean value
NF EN ISO 9239-1	CREATION 55 ARTE (site 004)	3	Critical heat flux (kW/m <sup>2</sup> )	10,5
			Smoke (% X min)	178,5

#### 4. Classification and field of application

##### 4.1. Reference of classification

This classification has been carried out in accordance with EN 13501-1 (2018).

##### 4.2. Classification

Fire behaviour		Smoke production
B <sub>n</sub>	-	s1

**Classification : B<sub>n</sub> – s1**

##### 4.3. Field of application

This classification is valid for the following end use applications :

Glued over a wood panel particle board without flame retarded classified C<sub>n</sub>-s1 with a density ≥ 510 kg/m<sup>3</sup> and over a fibre-cement A1<sub>n</sub> or A2<sub>n</sub> class with a density ≥ 1350 kg/m<sup>3</sup>.

This classification is valid for the following product parameters :

- A nominal mass per unit area of : 3850 g/m<sup>2</sup>
- A nominal thickness of : 2,50 mm
- A nominal thickness wear layer : 0,55 mm

#### 5. Limitations

This classification document does not represent type approval or certification of the product.

“The classification assigned to the product in this report is appropriate to a declaration of conformity by the manufacturer within the context of system 3 of AVCP and CE marking under the Regulation 305/2011/EU of the European Parliament and of the Council of 9 March 2011 laying down harmonised conditions for the marketing of constructions products.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.”

For the SARL C.R.E.T.  
The Technical Director  
Marc WELCOMME



*End of the classification report*