


DESCRIPTION						
Total Thickness	EN ISO 24346	mm	4.50			
Thickness of the wearlayer	EN ISO 24340	mm	0.55			
Weight	EN ISO 23997	g/sqm	7500			
Size	EN ISO 24342	mm	228.6x1220	152x914	600x600	914.4x914.4
Number of planks /tiles and sqm per box	-	-	6 / 1.67 sqm	12 / 1.67 sqm	6 / 2.16 sqm	4 / 3.34 sqm
CLASSIFICATION						
Norm/Product Specification	-	-	EN ISO 10582			
	ASTM F 1700	-	Class III Type B			
European Classification	EN ISO 10874	class	33 - 42			
Fire Rating	EN 13 501-1	class	Bfl-s1			
Static Electrical Propensity	EN 1815	kV	< 2			
Slip Resistance Wet	DIN 51 130	class	R10			
PERFORMANCES						
Wear Resistance	EN 660.2	mm ³	≤ 2.0			
Wear Group	-	group	T			
Type Binder content	ISO 10582	group	I			
Room Impact	NF S 31074	dB	74			
Impact sound insulation	EN ISO 717-2	dB	7			
Dimensional stability (norm)	EN ISO 23999	%	≤ 0.15			
Dimensional stability (average measured value)	-	%	≈ 0.05			
Residual Indentation	EN ISO 24343-1	mm	≤ 0.10			
Castor chair test	ISO 4918	-	OK			
Thermal Conductivity	EN ISO 10456	W/(m.K)	0.25			
Colour Fastness	EN 105 - B02	degree	≥ 6			
Surface Treatment	-	-	Protecshield®			
Chemical Products Resistance	EN ISO 26987		OK			
ENVIRONMENT / INDOOR AIR QUALITY						
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10			
CE MARKING						
	EN 14041		