



Gerflor USA Commercial Adhesive Chart

GERFLOR COMMERCIAL PRODUCTS										ADHESIVE CHART - COVERAGE - MOISTURE LIMITS						
Adhesives	RH Limit (ASTM F2170)	CC Limit (ASTM F1869)	pH Limit	Size	Trowel notch	Coverage per Pail or Can of Adhesive	Mipolam, Taralay	Tarasafe & H2O	LVT: Creation, Continuum, SAGA2	Mipolam Biocontrol ELS & ESD+	Mipolam Technic ELS & GTI Cleantech ELS	Mipolam Evo & Creation Evo	GTI, GTI MAX, Attraction, Creation Connect, Solid Clic & Clic	GTI MAX Cleantech Cleanroom	Linoleum	SPM Wall Panels
Gerfix NDT Tape	98%	15 lbs.	12	2.46' x 98.42' / 2" x 98.42'	None	250 sq ft										
Gerfix TPS+ (acrylic)	95%	10 lbs.	11	4 US Gal.	1/32" x 1/16" x 1/32" 'U'	680 to 880 sq. ft./ pail										
Gerfix Resilient Spray	95%	8 lbs.	11	21 oz. Can	None	150 to 167 sq. ft./ can										
Gerfix LVT & Plank Spray	95%	8 lbs.	11	21 oz. Can	None	150 to 167 sq. ft./ can										
Gerflor T-111 (polyurethane)	95%	8 lbs.	11	1.9 US Gal.	1/32" x 1/16" x 1/32" 'U'	320 to 420 sq. ft./ pail		Wet Areas								
Gerflor T-111 (polyurethane)	95%	8 lbs.	11	1.9 US Gal.	3/32" x 3/32" x 3/32" 'V'	135 to 150 sq. ft./ pail										Non-porous
Gerflor 313 Linoleum Adhesive	90%	8 lbs.	11	4 US Gal.	1/16" x 1/16" x 1/16" Square	400 to 500 sq. ft./ pail										
Gerflor 505 SPM Wall Adhesive	N/A	N/A	N/A	4 US Gal.	3/32" x 3/32" x 3/32" 'V'	280 to 320 sq. ft./ pail										Porous
Gerfix 196 (2-part Hybrid Acrylic)	98%	15 lbs	12	2.5 US Gal.	1/32" x 1/16" x 1/32" 'U'	425 to 550 sq. ft./ pail										
Gerfix 196 (2-part Hybrid Acrylic)	98%	15 lbs	12	2.5 US Gal.	1/16" x 1/16" x 1/16" Square	200 to 250 sq. ft./ pail										

Gerflor's Position on Moisture Testing

- Gerflor requires concrete slab moisture testing for any adhesive that is not rated for 100% RH
- Gerflor recognizes 2 methods to measure the moisture in a concrete slab: ASTM F2170 (RH) test and ASTM F1869 Calcium Chloride (CC) test
- It is always recommended to conduct both tests, and all tests need to meet the stated moisture limits
- If only one type of test is performed, Gerflor prefers the ASTM F2170 test method
- If Gerflor conducts an inspection on a moisture-related failure, we reserve the right to perform both tests

Color Legend
Green = Approved
Yellow = Needs Technical approval
Red = NOT approved



Gerflor USA Sport Products Adhesive Chart

GERFLOR SPORT PRODUCTS						ADHESIVE CHART - COVERAGE - MOISTURE LIMITS							
Adhesives	RH Limit (ASTM F2170)	CC Limit (ASTM F1869)	pH Limit	Size	Trowel notch	Coverage per pail or can of adhesive	Recreation Range	Taraflex Range	Sport M Comfort	Taraflex Dry-Tex	Isolsport	Vinyl BleacherBlok® SV	Surface to Bleacher Blok
Gerfix TPS+ (acrylic)	95%	10 lbs.	11	4 US Gal.	1/32" x 1/16" x 1/32" 'U'	680 to 880 sq. ft./ pail							
Gerfix Resilient Spray	95%	8 lbs.	11	21 oz. Can	None	150 to 167 sq. ft./ can							
Gerflor T-111 (polyurethane)	95%	8 lbs.	11	1.9 US Gal.	1/32" x 1/16" x 1/32" 'U'	320 to 420 sq. ft./ pail							
Gerfix 196 (2 part Hybrid Acrylic)	98%	15 lbs.	12	2.5 US Gal.	1/32" x 1/16" x 1/32" 'U'	425 to 550 sq. ft./ pail							
Gerpur (urethane)	100%	25 lbs.	14	2.5 US Gal.	1/16" x 1/16" x 1/16" Square	200 to 250 sq. ft./ pail							
Gerfix 100 (urethane)	100%	25 lbs.	14	2 US Gal.	1/32" x 1/16" x 1/32" 'U'	340 to 440 sq. ft./ pail							

Color Legend
Green = Approved
Yellow = Needs Technical approval
Red = NOT approved

Gerflor's Position on Moisture Testing

- Gerflor requires concrete slab moisture testing for any adhesive that is not rated for 100% RH
- Gerflor recognizes 2 methods to measure the moisture in a concrete slab: ASTM F2170 (RH) test and ASTM F1869 Calcium Chloride (CC) test
- It is always recommended to conduct both tests, and all tests need to meet the stated moisture limits
- If only one type of test is performed, Gerflor prefers the ASTM F2170 test method
- If Gerflor conducts an inspection on a moisture-related failure, we reserve the right to perform both tests



Products	Products									
	Gerfix NDT Tape	Gerfix TP5+	Gerfix Spray	Gerfix LVT Spray	Gerflor T-111	Gerpur	Gerfix 313	Gerfix 505	Gerfix 196	Gerfix 100
Creation WellPoint, Creation GuidePoint, Creation GrovePoint, & SAGA ²	X	X		X	NTP				X	
Creation Clic 28, Creation 70 Clic & Creation 22 Solid Clic		NTP		X	NTP				NTP	
DLW Linoleum						X			X	
Mipolam BioControl EL5 & ESD+	X	X	X							
Mipolam Technic EL5	X	X		X						
GTI MAX Connect, Attraction, Creation Connect, GTI PURE Connect	X	NTP		X	NTP				NTP	
GTI MAX Cleantech Cleanroom	X	X		X	NTP				X	
GTI Cleantech ESD	X	X		X						
Mipolam Affinity	X	X	X		X				X	
Mipolam Biocontrol Performance	X	X	X		X				X	
Mipolam Biocontrol Clean	X	X	X		X				X	
Mipolam Elegance	X	X	X		X				X	
Mipolam Symbioz ¹	X	X	X		X				X	
Mipolam Troplan	X	X	X		X				X	
Mipolam Planet	X	X	X		X				X	
Mipolam Evo & Creation Evo	X				NTP				X	
Taralay Impression	X	X	X		X				X	
Taralay Premium	X	X	X		X				X	
Mipolam SPM Wall Panels					X		X			
Taraflex Multi-Use 6.2, Sport M Plus & Sport M Performance		X	X		X				X	
Recreation 45, 60 & 85		X	X						X	
Recreation & Taraflex Surface					X					
Over Isolsport (Taraflex Multi-Use 6.2, Sport M Plus & Performance)					NTP				X	
Taraflex Sport M Plus Dry-Tex & Sport M Performance Dry-Tex		NTP	NTP			X			NTP	
Vinyl BleacherBlok® SV (Taraflex & Recreation)					X					X
Taraflex Sport M Comfort									X	
Tarasafe Ultra & H2O	NTP	NTP	NTP		X				NTP	

NTP = Needs Technical Approval

	ASTM F1869 Calcium Chloride (CaCl)	ASTM F2170 Relative Humidity Test (RH)
Installation:	Three tests for the 1st 1000 sq.ft. One additional test for each 1000 sq. ft. thereafter	Three tests for the 1st 1000 sq.ft. One additional test for each 1000 sq. ft. thereafter
Exposure Time	Minimum of 60 hours and a maximum of 72 hours	72 hours for the first tests. Subsequent test must stabilize with no drift on meter in a 5 minute period per ASTM F 2170
Use:	Moisture Vapor escaping from concrete and pH test	Relative humidity in the concrete
Test Range:	0.00 to 30.00 lbs	0 to 100% Relative Humidity
Plus:	Give an actual reading of water vapor escaping from the concrete slab	Give an actual reading of the relative humidity of the concrete slab
Recommendation	Test substrate using both tests RH and CaCl. Should you use only one, RH testing is the preferred method	