

DESCRIPTION

Total thickness	EN ISO 24346	mm	2,40
Thickness of wearlayer	EN ISO 24340	mm	1,12
Weight	EN ISO 23997	g/m ²	2890
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	m	20

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	classe	34 - 43
Fire rating	EN 13 501-1	classe	B _f -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	EN 16165:2021 – Appendix B (DIN 51 130)	classe	R12

PERFORMANCES

Wear resistance	EN 660.2	mm ³	≤ 2
Wear group	-	group	T
Type binder content	EN ISO 10582	type	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.10
Residual indentation (average measured value)		mm	~ 0.03
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0,25
Colour fastness	EN ISO 105 - B02	degré	≥ 6
Chemical products resistance	EN ISO 26987	-	OK
Anti-bacterial activity (MRSA) (1)	ISO 22196	-	> 99% Inhibits growth

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100
Certification	-	-	Floorscore®

CE MARKING

	EN 14041		
		-	

(1) The implementation of an effective cleaning regime is the best defence against infection