

TECHNICAL DATA SHEET

TARASAFE H2O

TARASAFE H2O

Description

Total thickness	ISO 24346 (EN 428)	mm	2.00
Thickness of wearlayer	ISO 24340 (EN430)	mm	0.85
Weight	ISO 23997 (EN426)	g/m ²	2350
Width/length of sheet	ISO 24341 (EN426)	cm / lm	200 / 20
Colour references	-	-	8

Classification

European classification	ISO 10874 (EN685)	class	34-43
Fire rating	AS ISO 9239-1-2013	kW / m ²	8.9
		smoke% / min	132
Static electrical propensity	EN 1815	kV	≤ 2
Slip rating oil wet-ramp	AS 4586 2013 (Appendix D)	class	R11
Slip rating oil wet pendulum	AS 4586 2013 (Appendix A)	class	P5
Slip rating wet barefoot ramp	AS 4586 2013 (Appendix C)	class	B
Surface roughness	µm	class	Rz ≥ 20

Performance

Abrasion resistance	EN 660.2	mm ³	≤ 2
Abrasion group	-	group	T
Dimensional stability	ISO 23999 (EN 434)	%	≤ 0.40
Residual indentation	ISO 24343-1 (EN 433)	mm	≤ 0.10
Castor chair test (type W)	ISO 4918 (EN 425)	-	Good
Thermal conductivity	ISO 10456 (EN 12524)	W/(m.k)	0.25
Colour fastness	ISO 105 - B02	degree	≥ 6
Chemical product resistance	ISO 26987 (EN 423)	-	Good
Surface treatment	-	-	SparClean®

Environment / Indoor Air Quality

TVOC after 28 days	-	µg/m ³	< 100
Recycled content	-	%	29
Certification	Floorscore®, GreenRate Level A, BEPPVC		
EPD	Yes		

(1) The implementation of an effective cleaning regime is the most important defence against infections.