

TECHNICAL DATA SHEET

TARASAFE ULTRA

TARASAFE ULTRA

Description

Total thickness	ISO 24346 (EN 428)	mm	2.00
Thickness of wearlayer	ISO 24340 (EN430)	mm	0.85
Weight	ISO 23997 (EN426)	g/m ²	2460
Width/length of sheet	ISO 24341 (EN426)	cm / lm	200 / 20
Colour references	-	-	18

Classification

European classification	ISO 10874 (EN685)	class	34-43
Fire rating	AS ISO 9239-1-2013	kW / m ²	9.2
		smoke% / min	140
Static electrical propensity	EN 1815	kV	≤ 2
Slip rating oil wet-ramp	AS 4586 2013 (Appendix D)	class	R10
Slip rating oil wet pendulum	AS 4586 2013 (Appendix A)	class	P4
Surface roughness	µm	class	Rz ≥ 20

Performance

Abrasion resistance	EN 660.2	mm ³	≤ 2
Abrasion group	-	group	T
Dimensional stability	ISO 23999 (EN 434)	%	≤ 0.40
Residual indentation	ISO 24343-1 (EN 433)	mm	≤ 0.03
Castor chair test (type W)	ISO 4918 (EN 425)	-	Good
Thermal conductivity	ISO 10456 (EN 12524)	W/(m.k)	0.25
Colour fastness	ISO 105 - B02	degree	≥ 6
Chemical product resistance	ISO 26987 (EN 423)	-	Good
Surface treatment	-	-	SparClean®

Environment / Indoor Air Quality

TVOC after 28 days	-	µg/m ³	< 100
Recycled content	-	%	29
Certification	Floorscore®, GreenRate Level A, BEPPVC		
EPD	Yes		

(1) The implementation of an effective cleaning regime is the most important defence against infections.