

TECHNICAL DATA SHEET

KENBROCK CUSHIONWOOD XL

KENBROCK CUSHIONWOOD XL

Description

Total thickness	ISO 24346 (EN 428)	mm	4.50
Thickness of wearlayer	ISO 24340 (EN 429)	mm	0.55
Weight	ISO 23997 (EN 430)	g/m ²	7422
Tile format	ISO 24342 (EN 427)	mm	228 × 1524
Product per carton		tiles / m ²	7 / 2.44
Product per pallet		boxes / m ²	48 / 117.12
Colour references			10

Classification

Norm/Product Specification			EN649	
European Classification		ISO 10874 (EN 685)	class	33-42
Fire rating		AS 5637.1-2015	kW / m²	9.9
			M²/kg	171
Static electrical propensity		EN 1815	kV	≤ 2
Slip rating -Emboss 1	oil wet-ramp	AS 4586 2013 (Appendix D)	class	R10
	oil wet pendulum	AS 4586 2013 (Appendix A)	class	P2
Slip rating -Emboss 2	oil wet-ramp	AS 4586 2013 (Appendix D)	class	R10
	oil wet pendulum	AS 4586 2013 (Appendix A)	class	P3

Performance

Wear Group	EN 649	-	T
Dimensional stability	ISO 23999 (EN 434)	%	≤ 0.10
Residual indentation	ISO 24343-1 (EN 433)	mm	0.05
Impact sound insulation	AS ISO 717-2-2004	LnTw	55
Colour fastness	ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR

Environment / Indoor Air Quality

TVOC after 28 days	ISO 16000 - 6	µg/m ³	≤100
Certification			GreenRate Level A, HealthRate Platinum

(1) The implementation of an effective cleaning regime is the most important defence against infections.

(2) Semi Wild emboss is on colour references 1650, 1651, 1652, 1653 & 1654. Semi Wild 2 emboss is on colour references 1655, 1656, 1657 1658 & 1659.